



Product Data Sheet

AmberSep™ IRC748 Chelating Resin Industrial-grade Chelant for Chemical Processing

Description

AmberSep™ IRC748 Chelating Resin is a macroporous resin containing iminodiacetic groups. The chemical nature of these groups is such that they form complexes with metal ions. It is highly resistant to osmotic shock and has excellent physical stability. This resin features a hetero-dispersed particle size distribution so it is well-suited for systems which are not constrained by pressure drop.

AmberSep™ IRC748 features very high capacity for calcium and is especially useful when treating brines that have a high strontium content. Under these conditions, the resin offers an improved cycle time, displaying also very good removal efficiency for strontium with very low metal leakage.

AmberSep™ IRC748 is also used for metal recovery in hydrometallurgical applications because it also exhibits high selectivity for heavy metal cations over alkali metal ions found in various process and waste streams.

Applications

- Chlor-alkali (brine purification)
- Electronics (printed wiring boards)
- Electroplating
- Process streams (trace metal removal)
- Hydrometallurgy (recovery of heavy metals from leach streams)

Typical Properties

Physical Properties	
Copolymer	Styrene-divinylbenzene
Matrix	Macroporous
Type	Chelant
Functional Group	Iminodiacetic acid
Physical Form	Beige, hard, opaque, spherical beads
Chemical Properties	
Total Exchange Capacity	1.35 eq/L
Dry Weight Capacity	≥ 4.45 eq/kg
Water Retention Capacity	60 – 65%
Particle Size §	
Particle Diameter	500 – 650 µm
Uniformity Coefficient	≤ 1.7
< 300 µm	≤ 1.0%
> 1000 µm	≤ 5.0%
Stability	
Whole Uncracked Beads	≥ 95%
Swelling	H ⁺ → Na ⁺ : 30%
Density	
Shipping Weight	750 g/L

§ For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 45-D00954-en).

Suggested Operating Conditions

Maximum Operating Temperature	90°C (194°F)	
Operating pH Range	1.5 – 14 (depends on the application)	
Flowrates		
Service	6 – 32 BV*/h (0.75 – 4 gpm/ft ³)	
Regeneration	2 – 4 BV/h (0.25 – 0.50 gpm/ft ³)	
Regenerant	HCl	H ₂ SO ₄
Concentration	5 – 10%	5 – 10%
Conversion to Na ⁺ form	1 – 4% NaOH at flowrate of 2 – 4 BV/h	

* 1 BV (Bed Volume) = 1 m³ solution per m³ resin or 7.5 gal per ft³ resin

Hydraulic Characteristics

Bed expansion of AmberSep™ IRC748 Chelating Resin as a function of backwash flowrate and temperature is shown in Figure 1.

Pressure drop data for AmberSep™ IRC748 as a function of service flowrate and temperature in brine is shown in Figure 2.

Figure 1: Backwash Expansion

Temperature = 10°C, 20°C, 40°C






Figure 2: Pressure Drop

Temperature = 20°C, 60°C



Application Information

The apparent selectivity of any ion exchange resin for a given metal depends upon concentration, the presence of other species, and pH. This makes absolute selectivities very difficult to determine, especially for waste treatment applications. Because of this, laboratory testing is essential when a resin is required to selectively remove one or more types of metal ions. In general, the selectivity for AmberSep™ IRC748 Chelating Resin follows the following order:



The affinity for H⁺ at pH 4 is situated between Cu²⁺ and Pb²⁺. Consequently, for the metals with selectivities less than Cu²⁺, the resin should be in the salt form (for example, in the Na⁺ form) to minimize metal leakage. At pH 2, the resin will be extensively in the H⁺ form and will only efficiently remove Fe³⁺, Hg²⁺, and Cu²⁺. Selectivity at various pH conditions for AmberSep™ IRC748 are given below:

The resin can operate in a neutral, acidic, or alkaline medium, but since its capacity depends on the pH, the following minimum pH values are recommended for various cations:

pH = 2		pH = 4		pH = 9 †	
Metal Ion	K (M/Ca)	Metal Ion	K (M/Ca)	Metal Ion	K (M/Ca)
Fe ³⁺	325 000	Hg ²⁺	2 800	Ni ²⁺	30
Cu ²⁺	130 000	Cu ²⁺	2 300	Cd ²⁺	14
Hg ²⁺	> 43 000	Pb ²⁺	1 200	Cu ²⁺	10
		Ni ²⁺	57	Zn ²⁺	3
		Zn ²⁺	17	Ca ²⁺	1.0
		Cd ²⁺	15		
		Co ²⁺	6.7		
		Fe ²⁺	4.0		
		Mn ²⁺	1.2		
		Ca ²⁺	1.0		

† Very high ammonium background, 200 g/L (NH₄)₂SO₄

Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2023 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

