



# DuPont™ AmberLite™ EV2X

## Gel, Ion Exchange Resin

### Key Features

- Translucent insoluble beads
- Optimized to purify glycol-coolant with minimal additive uptake Enhanced thermal stability leveraging DuPont's patented resin technology
- Retains excellent operating capacity over 500 hrs

### Key Applications

- Battery coolant purification
- Fuel Cell coolant purification
- Electric vehicle recharging station coolant purification
- Designed for light & heavy-duty vehicles
- For conductivity levels < 3 µS/cm
- For temperatures up to 105 °C

### Typical Properties

Physical Properties	
Copolymer	Crosslinked DVB
Matrix	Gel
Physical Form	Translucent, spherical beads
Cation/Anion Mixture	
Particle diameter	600 – 750 µm
Fines	< 300 µm < 1%
Metal content Fe	< 50 ppm/kg
Metal content Cu	< 10 ppm/kg
Heavy metals	< 10 ppm/kg
Swelling (HGa)	2.5%
Shipping Weight	695 g/L

### Suggested Operating Conditions


Maximum Peak Load FC Stack	105°C
pH Range (Stable)	1 – 14
Installed Total Capacity (min)	1000 meq/liter
Typical Total Capacity Utilization Factor (90°C)	> 90% (at 1000 hrs)
Typical Thermal Degradation Factor (90°C)	> 90% (at 1000 hrs)
Typical Loss of strong base functionality (90°C)	< 7% (at 1000 hrs)
Operational capacity estimate per liter of mixed bed resin	1000 x 0.9 x 0.9 x 0.93 meq

### General Information

- For additional information about AmberLite™ EV2X resin storage and handling, please refer to the [Resin Storage Conditions](#) (Form No. 45-D01093-en)

### Important Information

- AmberLite™ EV2X resin is a high purity polymeric. To avoid contamination, it needs to be stored and handled according to the DuPont operational guidelines.
- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.



All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DUPONT ASSUMES NO OBLIGATION OR LIABILITY FOR THE INFORMATION IN THIS DOCUMENT. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

