



Ion Exchange

Steam Generator Blowdown

A steam generator blowdown (SGBD) system purifies the water in steam generators to minimize corrosion and reduce ionic hideout. A low percentage of the total flow is directly removed from the steam generators and treated by ion exchange. The run length of the resin bed is determined by sodium leakage or other impurities; therefore, ion exchange resins must have high capacity and high selectivity for the impurities to be removed.

PRODUCT	FEATURES AND RECOMMENDED USES	TYPE	MATRIX	MINIMUM TOTAL VOLUME CAPACITY (eq/L)	IONIC FORM AS SHIPPED
DuPont™ AmberLite™ IRN99 H	Premium 16% DVB uniform particle size cation resin with very high Na selectivity, total capacity, and oxidative stability. Provides long resin life when operating in the amine form. Ready to use resin for non-regenerable units. Highly controlled for low sodium traces.	SAC	GEL	2.50	H+
DuPont™ AmberLite™ IRN97 H	High capacity 10% DVB uniform particle size cation resin for plants operating in the H/OH cycle or in the ammonia cycle. Ready to use resin for non-regenerable units. Highly controlled for low sodium traces.	SAC	GEL	2.10	H+
DuPont™ AmberLite™ IRN77 H	Uniform particle size gel cation resin processed to the highest purity standards required for treating water in the nuclear power industry.	SAC	GEL	1.90	H+
DuPont™ AmberLite™ IRN9652 H	High capacity 20% DVB macroporous cation resin. Highest selectivity for Na in organic amine form operation providing the longest resin life, mainly in morpholine conditioning. Ready to use resin for non-regenerable units.	SAC	MACRO	1.95	H+
DuPont™ AmberLite™ IRN78 OH	Premium high solids uniform particle size anion resin with very high capacity. Specifically processed to minimize organic chloride content. Ready to use resin for non-regenerable units.	SBA	GEL	1.20	OH-
DuPont™ AmberLite™ HPR2000 H	20% DVB uniform particle size macroporous cation resin with very high Na selectivity and oxidative stability. Providing long resin life when operating in the amine form. Best used in regenerable mixed beds.	SAC	MACRO	1.70	H+
DuPont™ AmberLite™ HPR1600 H	Premium 16% DVB uniform particle size cation resin with very high Na selectivity, total capacity, and oxidative stability. The larger particle size of AmberLite™ HPR1600 H makes it the right choice when pressure drop is a concern. Best used in regenerable mixed beds.	SAC	GEL	2.40	H+
DuPont™ AmberLite™ HPR9000 OH	Macroporous anion resin providing excellent resistance to surface fouling. Best used in regenerable mixed beds.	SBA	MACRO	0.80	OH-
DuPont™ AmberLite™ IRN150 H/OH	Nuclear grade mixed bed composed of uniform particle size AmberLite™ IRN77 H and IRN78 OH on a 1:1 equivalent basis for full demineralization.	MB	GEL/GEL	1.90/1.20	H+/OH-
DuPont™ AmberLite™ IRN160 H/OH	High-capacity nuclear grade mixed bed composed of uniform particle size AmberLite™ IRN97 H and IRN78 OH on a 1:1 equivalent basis. Designed to minimize separation of anion and cation during installation and transfer.	MB	GEL/GEL	2.10/1.20	H+/OH-
DuPont™ AmberLite™ HPR650 H	Ready to use, high-capacity uniform gel type resin combination for normal operation in circuit #5 of VVER. This combination of high exchange capacity strong acid cation and strong base anion is the ideal combination for achieving high operating capacity. Best used in regenerable mixed beds.	SAC	GEL	2.00	H+
DuPont™ AmberLite™ HPR550 OH	Ready to use, high-capacity uniform gel type resin combination for normal operation in circuit #5 of VVER. This combination of high exchange capacity strong acid cation and strong base anion is the ideal combination for achieving high operating capacity. Best used in regenerable mixed beds.	SBA	GEL	1.10	OH-

Key:

SBA = Strong Base Anion
 SAC = Strong Acid Cation

Powering performance worldwide.

With a large global manufacturing footprint, strong R&D expertise and technical support services and systems, we supply high market volumes with high quality. DuPont partners with you, our customer, to understand unmet needs and develop tailored solutions.

TECHNICAL SERVICE, RESEARCH & DEVELOPMENT

Chauny, France*
Edina, MN, USA
Huzhou, China
Hyderabad, India
KAUST Jeddah, KSA
Midland, MI, USA
Shanghai, China Singapore
Tarragona, Spain*
Wilmington, DE, USA

COMMERCIAL OPERATIONS

Astana, Kazakhstan
Bangkok, Thailand
Beijing, China
Bogota, Colombia
Buenos Aires, Argentina
Budapest, Hungary
Dubai, UAE
Chengdu, China
Delhi, India
Edina, MN, USA
Guangzhou, China
HCM City, Vietnam
Hong Kong, China
Jakarta, Indonesia
Johannesburg, South Africa
Kuala Lumpur, Malaysia
Madrid, Spain

Manila, Philippine
Melbourne, Australia
Mexico City, Mexico
Midland, MI, USA
Moscow, Russia
Mumbai, India Nairobi,
Kenya
Paris, France São
Paulo, Brazil
Seoul, Republic of Korea
Pfaeffikon, Switzerland
Shanghai, China Singapore
Surubya, Indonesia Taipei,
Taiwan Tokyo, Japan
Warsaw, Poland

MANUFACTURING

Chauny, France
Edina, MN, USA
Fombio, Italy
Huzhou, China
Jubail Industry
City, Saudi
Arabia Midland,
MI, USA
Qingpu, China
Soma, Japan



Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DUPONT ASSUMES NO OBLIGATION OR LIABILITY FOR THE INFORMATION IN THIS DOCUMENT. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2023 DuPont. All right reserved