

Product Information

Specialty Lubricants

DOW CORNING

Molykote[®] L-8030 Semi-dry Lubricant

FEATURES

- Compatible with many plastics and elastomers
- Coating film is not sticky like grease after dried
- Wide surface coverage

BENEFITS

- Provide superior lubricity on most plastics and elastomers

COMPOSITION

- Perfluoro oil
- Polytetrafluoroethylene
- Fluoro Solvent

Quick dry lubricant for plastics

APPLICATIONS

- Lubrication of sliding parts of Camera, Audio-Visual equipment, Precision appliance, Office equipment such as printer, copy and fax machine.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Property	Unit	Result
Appearance		White
Temperature range	°C	-65 ~ 150
Specific Gravity		1.45
Non-volatile Contents	%	2.6
Plastic compatibility (1/4 Oval test) POM, PS, ABS		No crack
Co-efficient of friction		
POM vs PS		0.06
POM vs STEEL		0.06

DESCRIPTION

Molykote[®] L-8030 Semi-dry Lubricant is a liquid type specialty lubricant containing Perfluoro oil and Polytetrafluoroethylene which are uniformly dispersed in fluoro solvent.

After coated, it forms white, semi-dry coating film which is not sticky like grease.

Molykote L-8030 Semi-dry Lubricant will not influence to environment. *Molykote* L-8030 Semi-dry Lubricant has zero Ozone Depletion Potential (ODP) and its Global Warming Potential (GWP) is lower than the equivalent *Molykote*[®] product.

HOW TO USE

Apply by brush or dipping.

HANDLING PRECAUTIONS

PRODUCT SAFETY
INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEB SITE AT DOW CORNING.COM, OR FROM YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.

USABLE LIFE AND STORAGE

When stored at or below 40°C (104°F) in the original unopened containers, this product has a usable life of 36 months from the date of production.

PACKAGING INFORMATION

This product is available in 1kg.

Samples are available in 50g.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our Web site, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

We help you invent the future.™

molykote.com