



DOW FILMTEC™ Membranes

DOW FILMTEC NF90 Nanofiltration Elements for Commercial Systems

Features


The DOW FILMTEC™ NF90 membrane elements provide high productivity performance while removing a high percentage of salts, nitrate, iron and organic compounds such as pesticides, herbicides and THM precursors. The low net driving pressure of the NF90 membrane allows the removal of these compounds at low operating pressures.

Product Specifications

Product	Part Number	Applied Pressure psig (bar)	Permeate Flow Rate gpd (m ³ /d)	Minimum Salt Rejection (%)
NF90-2540	149982	70 (4.8)	680 (2.6)	97.0
NF90-4040	149983	70 (4.8)	2,000 (7.6)	98.7

1. Permeate flow and salt rejection based on the following test conditions: 2,000 ppm MgSO₄, 77°F (25°C) and 15% recovery at the pressure specified above.
2. Permeate flows for individual NF90-2540 elements may vary by -20% / +30%. NF90-4040 individual elements may vary -15% / +50%.
3. Developmental products available for sale.

Figure 1



FilmTec sells coupler part number 89055 for use in multiple element housings. Each coupler includes two 2-210 EPR o-rings, FilmTec part number 89255.

Product	Dimensions – Inches (mm)			
	A	B	C	D
NF90-2540	40.0 (1,016)	1.19 (30)	0.75 (19)	2.4 (61)
NF90-4040	40.0 (1,016)	1.05 (27)	0.75 (19)	3.9 (99)

1. Refer to DOW FILMTEC Design Guidelines for multiple-element systems.
2. NF90-2540 has a tape outer wrap. NF90-4040 has a fiberglass outer wrap.

1 inch = 25.4 mm

Operating Limits

• Membrane Type	Polyamide Thin-Film Composite
• Maximum Operating Temperature	113°F (45°C)
• Maximum Operating Pressure	600 psi (41 bar)
• Maximum Feed Flow Rate - 4040 elements	16 gpm (3.6 m ³ /hr)
• - 2540 elements	6 gpm (1.4 m ³ /hr)
• Maximum Pressure Drop - tape wrapped	13 psig (0.9 bar)
• - fibreglassed	15 psig (1.0 bar)
• pH Range, Continuous Operation ^a	2 – 11
• pH Range, Short-Term Cleaning (30 min.) ^b	1 – 12
• Maximum Feed Silt Density Index	SDI 5
• Free Chlorine Tolerance ^c	<0.1 ppm

^a Maximum temperature for continuous operation above pH 10 is 95°F (35°C).

^b Refer to Cleaning Guidelines in specification sheet 609-23010 for NF90.

^c Under certain conditions, the presence of free chlorine and other oxidizing agents will cause premature membrane failure. Since oxidation damage is not covered under warranty, DOW FILMTEC recommends removing residual free chlorine by pretreatment prior to membrane exposure. Please refer to technical bulletin 609-22010 for more information.

Important Information

Proper start-up of reverse osmosis water treatment systems is essential to prepare the membranes for operating service and to prevent membrane damage due to overfeeding or hydraulic shock. Following the proper start-up sequence also helps ensure that system operating parameters conform to design specifications so that system water quality and productivity goals can be achieved.

Before initiating system start-up procedures, membrane pretreatment, loading of the membrane elements, instrument calibration and other system checks should be completed.

Please refer to the application information literature entitled "Start-Up Sequence" (Form No. 609-02077) for more information.

Operation Guidelines

Avoid any abrupt pressure or cross-flow variations on the spiral elements during start-up, shutdown, cleaning or other sequences to prevent possible membrane damage. During start-up, a gradual change from a standstill to operating state is recommended as follows:

- Feed pressure should be increased gradually over a 30-60 second time frame.
- Cross-flow velocity at set operating point should be achieved gradually over 15-20 seconds.
- Permeate obtained from first hour of operation should be discarded.

General Information

- Keep elements moist at all times after initial wetting.
- If operating limits and guidelines given in this bulletin are not strictly followed, the limited warranty will be null and void.
- To prevent biological growth during prolonged system shutdowns, it is recommended that membrane elements be immersed in a storage solution.
- The customer is fully responsible for the effects of incompatible chemicals and lubricants on elements.
- Avoid static permeate-side backpressure at all times.
- Maximum two element length vessels for tape wrapped elements.

For more information, contact our Customer Information Group:

North America: 1-800-447-4369
Latin America: +55-11-5184-8722
Europe, Africa, +31-115-672-626
Middle East:
Asia Pacific: +86-21-3851-4988

www.dowwaterandprocess.com

Notice: The use of this product in and of itself does not necessarily guarantee the removal of cysts and pathogens from water. Effective cyst and pathogen reduction is dependent on the complete system design and on the operation and maintenance of the system.

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.** All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. Nothing in this document should be treated as a warranty by Dow.

