

#### **Product Data Sheet**

## **DuPont™ AmberLite™ FPA51 Ion Exchange Resin**

Food-grade, Macroporous, Weak Base Anion Resin

### **Description**

DuPont™ AmberLite™ FPA51 Ion Exchange Resin is a macroporous, weakly basic, anion exchange resin containing tertiary amine functionality on a crosslinked polystyrene matrix. It has been specifically designed for the purifying liquid food streams including starch-based sweeteners and can also be used in bioprocessing applications.

### **Nutrition Applications**

AmberLite™ FPA51 Ion Exchange Resin has been sized to be used both in the fixed bed system commonly used in the corn sweetener industry as well as moving bed systems and polishing mixed bed. It is suitable for the deashing, deacidification, and decolorization of glucose, fructose and related starch-based sweeteners and derivatives as well as gelatin and other food process streams such as fruit juices.

Its high level of porosity gives AmberLite™ FPA51 an excellent combination of physical stability and high operating efficiency resulting in long process cycle times compared to products having a higher static volume capacity. This porous network also provides a more complete adsorption and desorption of large organic molecules resulting in excellent color removal compared to other weak base anion exchange resins.

### **Bioprocessing Applications**

A number of different antibiotic classes have been isolated, chemically modified, and used extensively by physicians in treating infectious diseases. As most traditional antibiotics were derived from yeast or bacteria, their large-scale production is based on fermentation processes. AmberLite™ FPA51 Ion Exchange Resin can be used for the removal of organic color bodies in those downstream bioprocesses.

### **Applications**

- · Nutrition applications
  - Sweetener deashing
  - Sweetener deacidification
  - Sweetener decolorization
- Bioprocessing applications
  - Decolorization

# **Typical Properties**

| Physical Properties      |                                |
|--------------------------|--------------------------------|
| Copolymer                | Styrene-divinylbenzene         |
| Matrix                   | Macroporous                    |
| Туре                     | Weak base anion                |
| Functional Group         | Tertiary amine (≥ 85%)         |
| Physical Form            | Beige, opaque, spherical beads |
| Chemical Properties      |                                |
| Ionic Form as Shipped    | Free base (FB)                 |
| Total Exchange Capacity  | ≥ 1.3 eq/L                     |
| Water Retention Capacity | 56 – 62%                       |
| Particle Size §          |                                |
| Particle Diameter        | 490 – 690 μm                   |
| < 300 µm                 | ≤1.0%                          |
| > 1180 µm                | ≤2.0%                          |
| Stability                |                                |
| Swelling                 | FB → CI:25%                    |
| Density                  |                                |
| Shipping Weight          | 660 g/L                        |

<sup>§</sup> For additional particle size information, please refer to the Particle Size Distribution Cross Reference Chart (Form No. 45-D00954-en).

# Suggested Operating Conditions

| Maximum Operating Temperature | 100°C (212°F)                                      |
|-------------------------------|--|
| Bed Depth, min.               | 700 mm (2.3 ft)                                    |
| Flowrates                     |  |
| Service                       | 2 – 6 BV*/h (depending on syrup concentration)     |
| Backwash                      | See Figure 1                                       |
| Regeneration                  | 1 – 2 BV/h   |
| Slow Rinse                    | Regeneration flowrate for 2 BV                     |
| Fast Rinse (if applicable)    | Service flowrate for 5 – 10 BV (with condensate or |
|                               | softened water)                                    |
| Contact Time                  |  |
| Regeneration                  | ≥ 30 – 45 minutes                                  |
| Regenerant                    | NaOH   |
| Concentration                 | 4%   |
| Level                         | 60 g/L (3.8 lb/ft <sup>3</sup> )                   |

<sup>\* 1</sup> BV (Bed Volume) = 1 m<sup>3</sup> solution per m<sup>3</sup> resin or 7.5 gal per ft<sup>3</sup> resin

## **Hydraulic Characteristics**

Estimated bed expansion of DuPont™ AmberLite™ FPA51 Resin as a function of backwash flowrate and temperature is shown in Figure 1.

Estimated pressure drop for AmberLite™ FPA51 a function of service flowrate and viscosity is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean water and a well- classified bed.

Figure 1: Backwash Expansion

Temperature =  $5 - 60^{\circ}$ C (41 - 140°F)




Figure 2: Pressure Drop Viscosity = 1 - 10 cP

250

Pressure drop, LPa/meter of bed Visco, 10 cP 200 150 Visco, 5 cP 100 50 Visco, 1 cP 0 10 15 20 0 Service Flow Rate, m/h

# **Product Stewardship**

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

#### **Customer Notice**

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

• WARNING: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

### **Regulatory Note**

This product may be used in applications that need to comply with relevant regulations. In support of these applications, a Regulatory Information Package is available upon request. Please address your request to your sales team or the contact details provided in this Product Data Sheet.

Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2023 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ⁵M or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.



Page 4 of 4 Form No. 45-D00754-en, Rev. 4 February 2023