

Product Data Sheet

DuPont™ AmberLite™ MAC-3 H Ion Exchange Resin

Food Processing, Macroporous, Acrylic, Weak Acid Cation Exchange Resin

Description

DuPont™ AmberLite™ MAC-3 H Ion Exchange Resin is an acrylic, macroporous weak acid cation exchange resin that offers high exchange capacity, excellent regeneration efficiency, very good resistance to osmotic shock, and good chemical and physical stability.

AmberLite™ MAC-3 H is effective in removing temporary hardness (hardness associated with alkalinity) and dealkalization. It can also be used for recovery of metals. AmberLite™ MAC-3 H can be supplied in accordance to the TOC (Total Organic Carbon) requirements of the major European legislations for use in food and potable water applications. In such cases, a recommendation is given for resin conditioning before use.

Applications

- · Softening
- Dealkalization
- Demineralization

Properties

Physical Properties		
Copolymer	Crosslinked acrylic	
Matrix	Macroporous	
Туре	Weak acid cation	
Functional Group	Carboxylic acid	
Physical Form	White to off-white, opaque, spherical beads	
Chemical Properties		
Ionic Form as Shipped	H ⁺	
Total Exchange Capacity	≥ 3.8 eq/L	
Water Retention Capacity	44 – 52%	
Particle Size §		
300 - 1180 μm	≥90%	
Stability		
Whole Beads	≥ 90%	
Swelling	$H^+ \rightarrow Na^+: \sim 70\%$	
Density		
Particle Density	1.18 g/mL	
Shipping Weight	750 g/L	

[§] For additional particle size information, please refer to the Particle Size Distribution Cross Reference Chart (Form No. 45-D00954-en).

Suggested Operating Conditions

Maximum Operating Temperature (H+ form)	120°C (248°F)		
pH Range	5 – 14		
Bed Depth, min.	800 mm (2.6 ft)		
Flowrates			
Service	$5 - 50 \text{ m/h} (2 - 20 \text{ gpm/ft}^2)$		
Backwash	See Figure 1		
Regeneration			
HCI	1 – 10 m/h (0.4 – 4 gpm/ft²)		
H_2SO_4	$5 - 20 \text{ m/h} (2 - 8 \text{ gpm/ft}^2)$		
Displacement Rinse	Same flowrate as the regenerant		
Fast Rinse (if applicable)	$5 - 50 \text{ m/h} (2 - 20 \text{ gpm/ft}^2)$		
Total Rinse Requirement	3-6 BV*		
Regenerant	HCI	H ₂ SO ₄	
Concentration	1 – 5%	0.5 – 0.8%	

^{* 1} BV (Bed Volume) = 1 m³ solution per m³ resin or 7.5 gal per ft³ resin


Hydraulic Characteristics

Estimated bed expansion of DuPont™ AmberLite™ MAC-3 H Ion Exchange Resin as a function of backwash flowrate and ionic form at 25°C (77°F) is shown in Figure 1. The flowrate necessary to achieve a desired bed expansion for other water temperatures can be calculated with the provided equations.

Estimated pressure drop for AmberLite™ MAC-3 H as a function of service flowrate at 20°C (68°F) is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean water and a well-classified bed. Estimated pressure drop at other water temperatures can be calculated with the provided equations.

Figure 1: Backwash Expansion

Figure 2: Pressure Drop Temperature = 25°C (77°F) Viscosity = 2 - 12 cPapm/ft2 2 10 12 16 20 28 32 36 40 80 Pressure Drop 60 40 20 25 10 20 10 20 30 40 50 60 70 80 90 m/h m/h Linear Flow Rate Regenerated Linear Flow Rate ---- Exhausted



For other temperatures use:

 $\begin{aligned} & \textbf{F}_{\text{T}} = \textbf{F}_{25^{\circ}\text{C}} \ [1 + 0.008 \ (1.8 \text{T}_{^{\circ}\text{C}} - 45)], \text{ where } \textbf{F} \equiv \text{m/h} \\ & \textbf{F}_{\text{T}} = \textbf{F}_{77^{\circ}\text{F}} \ [1 + 0.008 \ (\textbf{T}_{^{\circ}\text{F}} - 77)], \text{ where } \textbf{F} \equiv \text{gpm/ft}^2 \end{aligned}$

For other temperatures use:

 $P_{T} = P_{20^{\circ}C} / (0.026T_{\circ}C + 0.48)$], where $P \equiv bar/m$ $P_T = P_{68^{\circ}F} / (0.014T_{\circ F} + 0.05)$], where $P \equiv psi/ft$

Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

WARNING: Oxidizing agents such as nitric acid attack organic ion exchange resins
under certain conditions. This could lead to anything from slight resin degradation to
a violent exothermic reaction (explosion). Before using strong oxidizing agents,
consult sources knowledgeable in handling such materials.

Regulatory Note

This product may be used in applications that need to comply with relevant regulations. In support of these applications, a Regulatory Information Package is available upon request. Please address your request to your sales team or the contact details provided in this Product Data Sheet.

Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

© 2023 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, sм or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

