

# DuPont 5029

POLYMER SILVER FOR SMARTCARD APPLICATION

## Technical Data Sheet

### Product Description

DuPont 5029 is a silver composition designed for the printing of coils or antenna in smartcard and RFID tags.

### Product Benefits

- High conductivity
- High print thickness in a single print
- Higher solids, lowest resistivity after lamination

### Processing

- **Screen Printing Equipment**  
Reel to reel, semi-automatic or manual
- **Substrate**  
Polyester, PVC, Polycarbonate, ABS, Polyimide
- **Screen Type**  
200 mesh stainless steel or 62T polyester screen
- **Typical Circuit Line Thickness**  
200 mesh stainless steel/15 $\mu$ m emulsion build up to achieve line thickness of 20-30 $\mu$ m  
62T polyester screen / 20 $\mu$ m emulsion build up to achieve line thickness of 18-22 $\mu$ m
- **Typical Cure Conditions Conveyor Oven**  
PVC substrates 15-30 minutes, at a peak temperature 50-60°C  
Polyester substrates 2-5 minutes, at a peak temperature 120-130°C
- **Lamination**  
This composition can be processed through standard card lamination processor. These processes significantly reduce the achieved resistance
- **Clean up solvent**  
Ethylene Glycol Diacetate

### Dry

Dry and cure in a well ventilated oven or conveyor dryer where the exhaust meets environmental regulations.

**Table 1**  
**Typical Physical Properties**

Test	Properties
Sheet Resistivity* [m $\Omega$ /sq/mil] After Drying	$\leq 15$
After Lamination	4 - 8

**Table 2**  
**Composition Properties**

Viscosity (Pa.s) Brookfield 1/2RVT, UC&S (SC4-14/6R), @10rpm, 25°C $\pm$ 0.2°C	35 - 50
Solids(150°C)[%]	82 - 86
Coverage (cm <sup>2</sup> /g) **	60 - 80
Thinner	DuPont 3610

\*Sheet resistivity; line thickness 25 $\mu$ m, substrate 160  $\mu$ m PVC.  
\*\*200 mesh stainless steel / 15 $\mu$ m emulsion

Table 1 & 2 show anticipated typical physical properties for DuPont 5029 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

### General

Performance will depend to a large degree on care exercised in screen printing. Scrupulous care should be taken to keep the composition, printing screens and other tools free of metal contamination. Dust, lint and other particulate matter may also contribute to poor yields. For additional processing and application details consult the "DuPont Smart Card Design Guide".

## Printing

The composition should be thoroughly mixed before use. This is best achieved by slow, gently, hand stirring with a clean burr-free spatula (flexible plastic or stainless steel) for 1-2 minutes. Care must be taken to avoid air entrapment.

The screen and emulsion thickness will strongly influence the thickness and definition of the printed circuit. Typically, polyester screens (62T-77T) with 20-25µm for DuPont 5029. Stainless steel screens may also be employed and will result in higher definition and thicker prints at a given mesh count. This will affect the achieved resistance. Normally only one print is needed to achieve the thickness. For very thick tracks, multiple prints may be utilized. In this case should be an intermediate drying stage.

For design with very fine lines at 150µm or less then the screen should be selected to give a thinner print as such line cannot be resolved consistently with thick prints.

The printer conditions should be set to maximize the print thickness. This means using a high print speed and setting a low squeegee pressure. Typically this paste can be printed at speeds from 30-60 cm/s. Printing should be performed in a clean and well ventilated area.

Note: optimum printing characteristics are generally achieved in the room temperature range of 20°C-23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing.

## Thinner

This composition is optimized for screen printing, thinning is not normally required. Use the DuPont recommended thinner for slight adjustments to viscosity or to replace evaporation losses. The use of too much thinner or the use of a non recommended thinner may affect the rheological behavior of the material and its printing characteristics. Refer to table-“Composition Properties”

## Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

## Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).



*The miracles of science™*

For more information on DuPont 5029 or other DuPont Microcircuit Materials products, please contact your local representative:

### Americas

DuPont Microcircuit Materials  
14 T.W. Alexander Drive  
Research Triangle Park, NC 27709  
Tel.: 800-284-3382

### Europe

Du Pont (U.K.) Limited  
Coldharbour Lane  
Bristol BS16 1QD  
U.K.  
Tel.: 44-117-931-3191

### Asia

DuPont Kabushiki Kaisha  
Sanno Park Tower, 11-1  
Nagata-cho 2-chome  
Chiyoda-ku, Tokyo 100-611  
Japan  
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd  
45, Hsing-Pont Road,  
Taoyuan, Taiwan 330  
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd  
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,  
Pudong New District, Shanghai 201203, China  
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.  
3~5th Floor, Asia tower #726,  
Yeoksam-dong, Gangnam-gu  
Seoul 135-719, Korea  
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited  
7th Floor, Tower C, DLF Cyber Greens,  
Sector-25A, DLF City, Phase-III,  
Gurgaon 122 002 Haryana, India  
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd  
1 HarbourFront Place, #11-01  
HarbourFront Tower One,  
Singapore 098633  
Tel.: 65-6586-3022

<http://mcm.dupont.com>

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”).  
NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



*The miracles of science™*

MCM5029 (12/2012)