

# DuPont 7292

PTC CARBON RESISTOR

## Technical Data Sheet

### Product Description

Carbon-based PTC resistor paste DuPont 7292 can be used in self-regulating heating circuits that operate at <80°C. The Positive Temperature Coefficient (PTC) of the cured film can be used to design circuits which heat up quickly to an equilibrium temperature and then stabilize at that temperature without external controls.

### Product Benefits

- Self-thermostating temperature control
- Power reduction at operating temperature
- Fast warm-up to operating temperature
- Thermal stability at 90°C for 24hrs
- Power on/off cycling stability - with rapid plateau
- Adhesive compatibility – wide range/choice available

### Self-Regulating Features

For heating/de-misting applications, the required heater resistance is designed around the approximate  $\sim 15\text{K}\Omega/\square$  paste by placing varying geometry resistors in series or parallel. Depending on the power applied and the ambient temperature when the circuit is powered up, it will rapidly heat and self-regulate at the designed operating temperature. At this point, a considerable increase in resistance will have occurred and a lower power consumption will result.

### Processing

#### Substrates

125 $\mu\text{m}$  print treated and heat stabilized polyester

#### Screen Printing Equipment

Semi-automatic or manual

#### Ink residence time on screen

> 1 hr

#### Screen Types

Polyester, stainless steel

#### Termination

DuPont PE825, DuPont PE826, DuPont 5025 or DuPont 5064H polymer thick film silver inks

#### Typical Cure Conditions

Box oven: 130°C for 10-20 minutes

Reel-to-reel: 140°C/2min

#### Typical Circuit Line Thickness Printed with 280 mesh Stainless Steel Screen

6-9 microns

#### Clean-up Solvent

Ethylene glycol diacetate

**Table 1**  
**Cured Properties**

Test	Properties
Sheet Resistivity $\text{K}\Omega/\text{sq}$	10.0 – 18.0
R Magnification Factor (25-85°C)	8 – 10x
Adhesion/Tape Pull (3M Scotch Tape #600)	No Material Transfer

This table shows anticipated typical physical properties for DuPont 7292 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

### Design Notes

While the chemical make-up of the DuPont composition 7292 is patented by DuPont, it is advisable to check that specific designs and applications do not infringe on any other patents. Heater circuits typically consist of DuPont 7292 carbon composition overprinted on a silver termination having inter-digitized tracks. The overprinted carbon composition forms a wide geometry resistor and the distance along the width (between the inter-digitized tracks) is generally used to target the final heater circuit resistance value. The gap (or spacing) between the silver tracks, determines the power density and consequently the heating characteristics of the circuit.

### Applying Power

When the heater circuit is powered, it will rapidly heat and self-regulate/equilibrate at a designated temperature. This equilibrium temperature is influenced primarily by a very large increase in circuit resistance, see Figure 1. This is non-linear and generally referred to as Resistance Magnification (or PTC effect). In addition, the equilibrium temperature can be altered by the design and more specifically, the spacing between the silver tracks. An example is given, where 7 heater temperatures are plotted, with each having a termination spacing from 0.5mm through to 2.3mm, see Figure 2. Within the first few power cycles, a permanent resistance shift is to be expected and the magnitude will be dependent, primarily on the maximum operating conditions. This has been found to be typically less than 10%. It may also result in a slight reduction in PTC performance consequently, it may be necessary to accommodate this shift within the initial design.

Better temperature stability can be expected from DuPont 7292, see figure 4. Improved stability can be seen though to 2000 cycles (Power on/off cycles) when comparing to its predecessor DuPont 7282.

### Hysteresis effect

After the removal of power from a heater circuit, the polymer PTC composition exhibits a hysteresis effect. This is basically a "time lag" in the circuits' ability to return to its original starting resistance. This does not affect the self-regulating performance but may result in erroneous resistance measurements.

**Table 2**  
**Physical Properties**

Test	Properties
Viscosity (Pa.s) [Brookfield RVT UC&SP, 10 RPM, 25°C]	15 – 70
Thinner	DuPont 8270

This table shows anticipated typical physical properties for DuPont 7292 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

### Compatibility of Adhesives

If an adhesive is used directly over the PTC composition, it is essential that the compatibility of the adhesive is tested to ensure that the performance of the heater is not compromised by any adhesive interactions. Adhesive incompatibility may result in erratic /excessive resistance shifts and/or significant changes in PTC characteristics. See Figure 3, for more details.

### Printing

The composition should be thoroughly mixed before use. This is best achieved by slow, gentle, hand stirring with a clean burr-free spatula (flexible plastic or stainless steel) for 1-2 minutes. Care must be taken to avoid air entrapment. Printing should be performed in a clean and well-ventilated area.

Note: optimum printing characteristics are generally achieved in the room temperature range of 20°C - 23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing. Refer to - "Processing Conditions".

### Drying

Allow prints to level at room temperature, then dry in a well-ventilated oven or conveyor dryer. Refer to - "Processing Conditions".

### Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.


### Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).




*The miracles of science™*

**Figure 1:  
Resistance Magnification (PTC Effect) vs Temperature**



**Figure 2:  
Equilibrium Temp vs Ag Termination Spacing**




**Figure 3  
Adhesive Compatibility Check**

Composition	Adhesive Type	Delta R - Post 85°C Heat Cycle
DuPont 7292	Lohmann DC249	0
	Mactac B2100	5%
	ARcare EL92734	5%
	Avery Dennison FT126	10%
	Avery Dennison HPA1902W	-5%

7292 has a more extensive range of compatible adhesives

**Figure 4  
Powered (12V) Cycling**



*The miracles of science™*

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with © or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”). NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



*The miracles of science™*

For more information on DuPont 7292 or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials  
14 T.W. Alexander Drive  
Research Triangle Park, NC 27709  
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited  
Coldharbour Lane  
Bristol BS16 1QD  
U.K.  
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha  
DuPont Electronic Center  
KSP R&D B213, 2-1, Sakado 3-chome, Takatsu-ku,  
Kawasaki-shi, Kanagawa, 213-0012, Japan  
Tel: +81-44-820-7575

DuPont Taiwan Ltd  
45, Hsing-Pont Road,  
Taoyuan, Taiwan 330  
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd  
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,  
Pudong New District, Shanghai 201203, China  
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.  
3~5th Floor, Asia tower #726,  
Yeoksam-dong, Gangnam-gu  
Seoul 135-719, Korea  
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited  
7th Floor, Tower C, DLF Cyber Greens,  
Sector-25A, DLF City, Phase-III,  
Gurgaon 122 002 Haryana, India  
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd  
1 HarbourFront Place, #11-01  
HarbourFront Tower One,  
Singapore 098633  
Tel.: 65-6586-3022

<http://mcm.dupont.com>