

DuPont 7401

GLASS ENCAPSULANT

Technical Data Sheet

Product Description

High temperature glass encapsulant composition DuPont 7401 is intended for use as an insulating and protective layer over hybrid circuits and resistor networks. DuPont 7401 has been designed to be compatible with DuPont 7400 surge resistor series. As well as providing a dense hermetic fired film. DuPont 7401 has been specifically formulated to allow resistors to be laser trimmed through the encapsulant. DuPont 7401 is applied to ceramic substrates by screen printing and fired in an air (oxidizing) atmosphere.

Product Benefits

- Lead, nickel, and cadmium free
- Blue color
- Thin, dense fired film
- Fired at a peak temperature of 850°C
- Provides excellent high voltage pulse stability when used in conjunction with DuPont 7400 series surge resistors
- Laser trimmable

Compatibility

Encapsulant DuPont 7401 is designed to be compatible with DuPont 7400 series surge resistor compositions.

Processing

Thinner

DuPont 7401 is optimized for screen printing and thinning is not normally required. DuPont 4553 thinner, may be used sparingly for slight adjustments to viscosity or to replace evaporation losses.

Table 1
Composition Properties

Test	Properties
Viscosity (Pa.S) <small>(Brookfield HBT, 10 rpm, SC4-14/6R, 25°C)</small>	100 - 250
Coverage ¹ (cm ² /g)	160 - 180
Thinner	DuPont 4553

¹based on a fired film thickness of 12µm

Table 1 shows anticipated typical physical properties for DuPont 7401 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Printing

Encapsulant composition DuPont 7401 should be thoroughly mixed before use. This is best achieved by slow, gentle hand stirring with a clean, burr-free spatula (flexible plastic) for 1-2 minutes. Care must be taken to avoid air-bubble entrapment. Printing should be carried out in a clean, well-ventilated area.

Note: optimum printing characteristics of DuPont 7401 are generally achieved in the temperature range 20°C - 23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing. DuPont 7401 encapsulant should be printed with a 325 mesh stainless steel screen, to obtain a fired thickness of 10-14µm.

Drying

Allow prints to level for 5-10 minutes at room temperature in a clean, environment, followed by drying for 10-15 minutes at 150°C in a well ventilated oven or conveyor dryer.

Firing

Fire in a well ventilated belt or conveyor furnace in air with a 30 minute cycle with a peak of 850°C held for 10 minutes (See figure 1). Predictable shifts in resistance values of DuPont 7400 series resistors will occur after encapsulation, typical changes are shown in the table below.

Care must be taken to ensure that any gases/vapors from other chemicals/materials (e.g. halogenated solvents) do not enter the furnace muffle. It is also essential that the air supply to the furnace is clean, dry and free of contaminants.

Air flows and extraction rates should be optimized to ensure the oxidizing conditions exist within the muffle, and that no furnace exhaust gases enter the room.

Laser Trimming

Laser trimming of resistors encapsulated with DuPont 7401 should be carried out at higher power setting than is normally used with low firing encapsulants. Typical conditions that have been used for DuPont 7401 encapsulant at 12µm fired thickness with DuPont 7400 series resistors are as follows: bite size 4-5 µm, pulse frequency 4-5kHz; average power 4.0-5.0 W, giving trim speeds of up to 25 mm/s.


General

Yields and performance will depend to a large degree on the care excised during processing, particularly in screen printing. Great care should be taken to keep the conductor composition, printing screens and other tools free of metal contamination. Dust, lint and other particulate matter may also contribute to poor yields.

Resistance change on overglaze firing ²	
Resistor	ΔR
7410	<5%
7420	<5%
7450	<5%
7499	<5%
743R	<10%

² Termination 7484 prefired using a 30 minute cycle. Resistor and encapsulant fired using a 30 minute cycle

Figure 1 - 30 Minutes Profile



Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).



The miracles of science™

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”).

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

For more information on DuPont 7401 or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-611
Japan
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3-5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFrong Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://mcm.dupont.com>