

DuPont 788X

SERIES HEATED GLASS COMPOSITION

Technical Data Sheet

Product Description

DuPont 788X Series Defogger Silver Paste is provided for use in the production of electrically heated backlights by a direct printing process. The pastes are screen-printed onto glass or black enamel and fired in fast fire glass furnaces. The resistance of the heater at constant voltage or current determines the power output. The resistance target is achieved by printing the silver paste to achieve the correct fired geometry (conductor length and cross-sectional area.) For a fixed conductor pattern, the resistance target is achieved through controlling the fired thickness either by changing printing conditions (for example screen mesh) or by changing the silver content in the printed paste by blending the DuPont 788X series members.

This system is not designed to be electroplated.

Product Benefits

- Lead and cadmium free system.
- Excellent conductivity with system capability for a wide range of resistivity.
- Uniform intense colour
- Excellent fired density giving good hiding power to clips soldered on to silver fired directory on glass (fired thickness > 7 µm).
- Long screen life.
- Robust printing performance.
- Fully blendable system

Processing

General

Yield and performance will depend to a large degree on the care exercised during processing, particularly in screen printing. Scrupulous care should be taken to keep DuPont 788X paste, printing screens and other tools free of metal contaminants. Dust, lint and other particulate matter may also contribute to poor yields.

Paste Preparation

DuPont 788X should be thoroughly mixed before use. This is best achieved by slow, gentle hand stirring with a clean, burr-free spatula (flexible plastic or stainless steel) for 1-2 minutes. Jar rolling paste is not appropriate for mixing and is not recommended.

In order to obtain a specific resistance value, the pastes can be blended with each other. DuPont 7885 low-solids paste is provided for blending only, and should not be printed alone.

Printing

DuPont 788x can be printed with 45T-110T polyester or 150-250 mesh stainless steel screens with terpene-resistant emulsion. Printing should be carried out in a clean, well-ventilated area. Note: optimum printing characteristics of DuPont 788X are generally achieved in the temperature range 20°C-23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing.

Drying

Dry with hot air at 150°C or with an infrared dryer to the required green strength.

Firing

Fire between 625°C and 700°C for 2 to 4 minutes, followed by cold-air tempering. To achieve the desired properties, the furnace atmosphere must be controlled to avoid both contamination (due to sulphur for example) and poor burnout of the organic species due to low oxygen availability. Firing is the critical step in achieving designed properties. Within the firing conditions quoted above, the resistance (resistance) will generally decrease with increasing firing temperature. Furthermore, some properties such as adhesion over glass or enamel will vary as a function of firing temperature.

Typical Physical Properties

| Test | Properties | | |
|--|-------------|-------------|-------------|
| | 7881 | 7882 | 7883 |
| Silver Content (%) | 80 | | |
| Solids(%) | 83.5 - 84.5 | 67.7 - 68.7 | 52.0 - 53.0 |
| Viscosity (Pa.s) [Brookfield RVT, SC-4-14/6R@ 10 rpm, 25°C] | 28 - 35 | 28 - 35 | 28 - 35 |
| Resitivity, (mΩ/sq @ 10 μm) | 2.6 - 3.4 | 2.8 - 5.2 | 3.0 - 6.0 |
| Thinner | DuPont 8250 | | |

Table 1 shows anticipated typical physical properties for DuPont 788X based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Soldering

Use 27Sn/70Pb/3A solder at 300-300°C and non-activated flux. To achieve good solder wetting, it is recommended that the surface of the fired silver to burnished with steel wool or fibreglass prior to soldering.

Compatibility

DuPont 788X Series has been tested with a wide variety of both infra-red and UV-curable lead free enamels, with no known incompatibilities. However, it is impossible or impractical to cover every combination of materials, customer processing conditions and circuit layout. It is therefore essential that customers thoroughly evaluate this material in their specific situations, in order to completely satisfy themselves as to the overall quality and suitability of the composition for its intended application (s).

Thinner

DuPont 788X is optimised for screen printing and thinning is not normally required. DuPont 8250 may be used sparingly for slight adjustments to viscosity or to replace evaporation losses. However, the use of too much thinner or the use of a non-recommended thinner may affect the rheological behaviour of the material and its printing characteristics.

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is three months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).



The miracles of science™

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with © or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates ("DuPont"). NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 ("Medical Applications Policy") and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user's consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data's accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user's responsibility to satisfy itself that the product is suitable for the user's intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

For more information on DuPont 788X or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-611
Japan
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3~5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://mcm.dupont.com>