

DuPont™ LuxPrint® 8152L

ELECTROLUMINESCENT MATERIAL

Technical Data Sheet

Product Description

DuPont™ LuxPrint® 8152L electroluminescent material is used in combination with DuPont EL Dielectrics and Conductors to fabricate electroluminescent lamps*. This composition is designed to provide a uniform layer of blue-green phosphor in a polymeric matrix when screen printed. The Long-Life composition utilizes microencapsulated phosphor powder and hydrophobic binders for excellent moisture protection and longer lamp lifetimes.

Product Benefits

- Encapsulated phosphor
- High light intensity
- Excellent moisture protection
- Ready for screen printing
- Compatible with LuxPrint® System
- Excellent adhesion to Indium Tin Oxide (ITO) sputtered polyester


Processing

- **Screen Printing Equipment**
Semi-automatic or manual
- **Substrates**
Polyester, ITO-Polyester (80Ω/sq), glass
- **Ink Residence Time On Screen**
>2 hours
- **Screen Types**
Polyester: 77T-62T;
Stainless Steel: 200 mesh
20-25µm emulsion
- **Typical Cure Conditions**
Box oven: 130°C/10 min.
Belt dryer: 130°C/90 sec.
- **Layer Thickness**
25 - 40 µm (dry)
- **Clean-up Solvents**
Ethylene Diacetate, Acetone
- **Coverage**
110 – 130 cm²/g

Table 1
Composition Properties

Test	Properties
Viscosity (Pa.s) [Brookfield ½RVT #14 @ 10rpm, 25°C]	10 - 20
Solids (150°C)(%)	73 - 76
Thinner	DuPont 8210
Paste Color	Cream
Color in Powered lamp	Blue-Green

Table 1 shows anticipated typical physical properties for LuxPrint® 8152L based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.



Tested at 100V, 400Hz

Table 2
Printed Properties on 125µm Polyester Film

Test	Properties
Coverage (cm ² /g)	120
Dry Layer Thickness (µm)	25 - 40

Printing

This composition must be thoroughly mixed before use. This is best achieved by slow, gentle, hand stirring with a clean, preferably plastic spatula for several minutes. Care must be taken to avoid air entrapment.

Printing should be performed in a clean and well ventilated area. Note: optimum printing characteristics are generally achieved in the room temperature range of 20°C-23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing.

Thinner

This composition is optimized for printing, thinning is not normally required. Use the DuPont recommended thinner for slight adjustments to viscosity or to replace evaporation losses. The use of too much thinner or the use of a non recommended thinner may affect the rheological behavior of the material and its printing.

Storage and Shelf Life

Containers may be stored in a clean, stable environment at room temperature (<25°C), with their lids tightly sealed. Storage in freezers (temperature <0°C) is NOT recommended as this could cause irreversible changes in the material. Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use. Phosphor particles tend to settle out during static storage. Gentle jar rolling or turning the jars may be used to minimize settling of the phosphor component.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

For more information on DuPont™ LuxPrint® 8152L electroluminescent material or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
Sanno Park Tower, 11-1
Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-611
Japan
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3~5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://www.mcm.dupont.com>



The miracles of science™

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”).
NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

MCM8152L(06/2012)