

DuPont™ LuxPrint® 9145

ELECTROLUMINESCENT MATERIALS

Technical Data Sheet

Product Description

DuPont™ LuxPrint® 9145 electroluminescent material is a silver conductor designed for use with DuPont™ LuxPrint® system for manufacturing screen-printed EL lamps. It is fully compatible with the phosphors, dielectrics and conductors of the system. LuxPrint® 9145 features excellent adhesion to indium-tin oxide (ITO), and may be employed in front bus bars and contacts as well the rear electrode in an EL lamp build.

Product Benefits

- Excellent adhesion to ITO
- High conductivity for high light intensity
- Low moisture affinity
- Compatible with the DuPont™ EL System

Processing

- **Screen Printing Equipment**
Semi-automatic or manual
- **Substrates**
Polyester, ITO-Polyester, DuPont EL Dielectric, Glass
- **Ink Residence Time On Screen**
>2 Hours
- **Screen Types**
200-280 mesh (line/sqin); 12 - 15 µm emulsion
- **Typical Cure Conditions**
Box oven: 5 min. at 130°C
- **Clean-up Solvent**
Carbitol Acetate or Ethylene Diacetate

Typical Physical Properties

Test	Properties
Viscosity (Pa-s) (Brookfield RVT#14 Spindle @ 10 RPM, 25°C)	20 - 100
Solids (%)[@ 150°C]	53 - 60
Thinner	DuPont 8211
Resistivity (mΩ/sq/25µm)	<50
Dry Layer Thickness (µm)	10 - 14

This table shows anticipated typical physical properties for LuxPrint® 9145 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Printing

LuxPrint® 9145 Silver Conductor should be thoroughly mixed before use. If it has been stored for several days, the paste may appear “coagulated”. Simply hand stir with a clean, burr-free spatula (flexible plastic) for 1 - 2 minutes until paste appearance returns to normal. Care must taken to avoid air entrapment. Printing should be carried out in a clean well ventilated area.

Note: optimum printing characteristics of LuxPrint® 9145 are generally achieved in the temperature range 20-23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing.

Thinner

DuPont Luxprint® 9145 is optimized for screen printing and thinning is not normally required. DuPont Electronics Composition Thinner 8211 may be used sparingly for slight adjustments to viscosity or to replace evaporation losses. However, the use of too much thinner or the use of a non-recommended thinner may affect the rheological behavior of the material and its printing characteristics.

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates ("DuPont"). NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 ("Medical Applications Policy") and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user's consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data's accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user's responsibility to satisfy itself that the product is suitable for the user's intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

For more information on DuPont™ LuxPrint® 9145 electroluminescent materials or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
DuPont Electronic Center
KSP R&D B213, 2-1, Sakado 3-chome, Takatsu-ku,
Kawasaki-shi, Kanagawa, 213-0012, Japan
Tel: +81-44-820-7575

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3-5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://mcm.dupont.com>