

DuPont LF152

CROSSOVER DIELECTRIC COMPOSITION

Technical Data Sheet

Product Description

DuPont LF152 is a filled, crystallizable screen-printed thick film dielectric composition and is an integral element of System LF. It is a lead free* dielectric intended for use in crossover applications

Product Benefits

- Lead, Cadmium, Chromium and Nickel Free*
- Broad conductor compatibility (gold, silver and mixed metal)
- Compatible with cofirable conductors
- Highly resistant to EMF (electro-motive force) blistering and shorting
- Robust electrical and mechanical properties
- Thin, 2 print, hermetic dielectric film for protection against environmental conditions, and mechanical abrasion

*Cadmium and lead "free" as used herein means that these are not intentionally added to the referenced product. Trace amounts however may be present.

Design Note

The optimum yield in the most demanding applications, it is recommended that a fired thickness of 30 μm or greater is achieved between conductor layers.

Processing Conditions

Printing

230 to 280 stainless steel screen, at a print speed of 15cm/sec.

Drying

Allow prints to level for 10-15 minutes at room temperature, and then dry for 10-15 minutes at 150°C.

Typical Physical Properties

Test	Properties
Viscosity (Pa.s) [Brookfield HBT, UC&SP, 50 rpm, 25°C]	55-120
Coverage (cm^2/g) [Based on average fired thickness of 14mm]	110-130
Thinner	DuPont 4553
Total Fired Thickness (mm)	> 30
Dielectric Constant (@1KHZ)	7-11
Dissipation Factor (@1KHZ)	<0.5%
Leakage Current ¹ [$\mu\text{A}/\text{cm}^2$]	<1
Insulation Resistance [30 μm]	>10 ¹² @ 100VDC
Breakdown Voltage [30 μm]	>1000V/30mm
EMF Blister Resistance ²	>30 firing
<small>¹ Standard measurements made after 5 minutes at 10VDC ² Measured deflection of 5 in by 1 in substrates with 5 circuit layers, single sided</small>	

This table shows anticipated typical physical properties for DuPont LF152 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Firing

850°C peak held for 10 minutes on 30 minutes cycle in an air atmosphere.

Recommended Processing Procedure Substrates

Substrates of different compositions and from various manufacturers may result in variation in performance properties.

Thinner

This composition is optimized for screen-printing, thinning is not normally required. Use the DuPont recommended thinner for slight adjustments to viscosity or to replace evaporation losses. The use of too much thinner or the use of a non-recommended thinner may affect the rheological behavior of the material and its printing characteristics. Refer to table 1.

Printing

The composition should be thoroughly mixed before use. This is best achieved by slow, gently, hand stirring with a clean burr-free spatula (flexible plastic) for 1-2 minutes. Care must be taken to avoid air entrapment. Printing should be performed in a clean and well-ventilated area. Note: optimum printing characteristics are generally achieved in the room temperature range of 20°C – 23°C. It is therefore important that the material, in its container, is at this temperature prior to commencement of printing.

Drying

Allow prints to level at room temperature, and then dry in a well-ventilated oven or conveyor dryer.

Firing

Fire in a well ventilated belt, conveyor furnace, or static furnace. Airflows and extraction rates should be optimized to ensure that oxidizing conditions exist within the muffle.

For more information on DuPont LF152 or other DuPont Microcircuit Materials products, please contact your local representative:

Americas

DuPont Microcircuit Materials
14 T.W. Alexander Drive
Research Triangle Park, NC 27709
Tel.: 800-284-3382

Europe

Du Pont (U.K.) Limited
Coldharbour Lane
Bristol BS16 1QD
U.K.
Tel.: 44-117-931-3191

Asia

DuPont Kabushiki Kaisha
DuPont Electronic Center
KSP R&D B213, 2-1, Sakado 3-chome, Takatsu-ku
Kawasaki-shi, Kanagawa, 213-0012
Japan
Tel.: 81-44-820-7575

DuPont Taiwan Ltd
45, Hsing-Pont Road,
Taoyuan, Taiwan 330
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,
Pudong New District, Shanghai 201203, China
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.
3-5th Floor, Asia tower #726,
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens,
Sector-25A, DLF City, Phase-III,
Gurgaon 122 002 Haryana, India
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One,
Singapore 098633
Tel.: 65-6586-3022

<http://mcm.dupont.com>



The miracles of science™

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”).
NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



The miracles of science™

MCMLF152 (3/2014)