



DUPONT™ TEMPRION™ EIF N SERIES

ELECTRICALLY INSULATING FILM

DESCRIPTION

DuPont™ Temprion™ EIF N Series is a flexible laminate film comprising an electrically insulating, puncture resistant Kapton® MT+ polyimide core coated with a high temperature stable, thermally conductive elastomer coating on one or both sides.

Temprion™ EIF features Kapton® MT+ polyimide as a carrier to achieve best-in-class thermal performance for an electrically insulating film, where electrically isolating components within a package is critical to operation.

APPLICATIONS

- Conventional Power Modules
- Discrete Power Devices
- Power Supplies

FEATURES

- Electrical insulation
- High temperature stability
- Low thermal resistance
- High puncture resistance
- UL 94 flammability rating (pending)
- RoHS Compliance

Table 1 – Typical Properties of DuPont™ Temprion™ EIF N Series Electrically Insulating Film

Property	NA037057D						Test Method
Total Thickness, mil (mm)	6 (0.15)						ASTM D374
Reinforcement Carrier	Kapton® 150MT+						–
Continuous Use Temp, °F (°C)*	-4 to 437 (-20 to 225)						–
Shore Hardness-A Scale**	75						ASTM D2240
Thermal Conductivity, W/m•K	1.20						ASTM D5470
Thermal Performance vs. Pressure							
Pressure, psi (MPa)	14.5 (0.1)	43.5 (0.30)	72.5 (0.5)	101.5 (0.7)	130.5 (0.9)	159.5 (1.1)	
Thermal Impedance, °C•in ² /W (°C•cm ² /W)	0.35 (2.30)	0.26 (1.65)	0.22 (1.45)	0.21 (1.35)	0.20 (1.29)	0.19 (1.26)	
Breakdown Voltage, Vac	> 6000						ASTM D149
Volume Resistivity, Ω•cm	> 10 ¹²						ASTM D257
Flammability	Pending						UL-94
RoHS Compliant	Yes						–

*High temperature range of continuous temperature usage determine by thermogravimetric analysis (24 h analysis).

**Shore hardness was measured on the elastomer coating

www.temprion.dupont.com

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo and DuPont™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-4.

K-29532 (7/17)