



DUPONT™ TEMPRION™ PGF N SERIES

PREFORMED GAP FILLER

DESCRIPTION

DuPont™ Temprion™ PGF-N Series are non-silicone elastomeric pads that feature high temperature stability with electrical insulation and high thermal conductivity.

Temprion™ PGF-N has been designed to deliver long term reliability for applications that require continuous operating temperatures up to 250°C.

APPLICATIONS

- Thermal Interface Material
- Power Electronics

FEATURES

- High temperature stability
- Non-silicone elastomer
- Low thermal resistance
- Electrical insulation
- UL 94 flammability rating (pending)
- RoHS Compliance

Table 1 – Typical Properties of DuPont™ Temprion™ PGF N Series Preformed Gap Filler

Property	N18 Series			N10 Series			Test Method
Thickness, mil (mm)	8 (0.2) – 40 (1.0)			8 (0.2) – 40 (1.0)			ASTM D374
Reinforcement Carrier	none						–
Continuous Use Temp, °F (°C)*	-4 to 482 (-20 to 250)						–
Thermal Conductivity, W/m•K	1.8			1.0			ASTM D5470
Thermal Performance vs. Pressure**							
Pressure, psi (MPa)	14.5 (0.1)	43.5 (0.30)	72.5 (0.5)	101.5 (0.7)	130.5 (0.9)	159.5 (1.1)	
Thermal Impedance, °C•in ² /W (°C•cm ² /W)**	0.67 (4.0)	0.58 (3.70)	0.55 (3.60)	0.51 (3.30)	0.48 (3.10)	0.45 (2.90)	
Breakdown Voltage, kVac/mm	15			13			ASTM D149
Volume Resistivity, Ω•cm	> 10 ¹⁰						ASTM D257
Flammability	Pending						UL-94
RoHS Compliant	Yes						–
Shore Hardness-A Scale	90			80			ASTM D2240

*Continuous operating temperature determined by thermogravimetric analysis (24 h dwell)

**Thermal impedance was measured PGF-N180500 and includes interfacial resistances.

www.temprion.dupont.com

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo and DuPont™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see “DuPont Medical Caution Statement,” H-50102-4. K-29535 (7/17)