



DUPONT™ KAPTON® 150FCRC019

TECHNICAL DATA SHEET

DESCRIPTION

DuPont™ Kapton® corona resistant film is a state of the art polyimide film that withstands the damaging effects of corona discharge. This coronal resistance provides improved service life and operational efficiencies vs conventional insulation materials.

Kapton® 150FCRC019 is a composite film consisting of Kapton® 100CRC corona resistant polyimide film and a heat fusible FEP fluoropolymer film. In addition to the corona resistant properties, Kapton® FCRC offers excellent, physical, electrical, thermal, and chemical resistant characteristics expected with Kapton® polyimide films.

Kapton® 150FCRC019 has been developed for use as a magnet wire insulation in rail traction, industrial motors and generators where there is a need for enhanced insulation life under partial discharge environments.

Kapton® FCRC may also be used in other electrically insulating applications where partial discharge may occur.

CHARACTERISTICS

- Corona resistant film
- Heat fusible adhesive
- High dielectric strength
- Reduced thickness versus mica laminates

APPLICATIONS

- Magnet wire
- Traction motors: rail, auto, mining
- Industrial motor insulation
- Wind, hydro generators
- ESP motors
- High temperature
- High reliability
- Aerospace and specialty wires

TABLE 1—TYPICAL PHYSICAL PROPERTIES OF DUPONT™ KAPTON® 150FCRC019 POLYIMIDE FILM

Property	Unit	Typical Value	Test Method
Thickness	mil	1.5	ASTM D-374
	µm	38	
Tensile Strength	kpsi	26	ASTM D-882
	MPa	179	
Elongation	%	90	ASTM D-882
Tensile Modulus	kpsi	330	ASTM D-882
	GPa	2.28	
Dielectric Strength	V/mil	4600	ASTM D-149
	kV/mm	181	
315 °C Heat Seal Strength	gms/in	1100	DuPont Test Method
	gms/cm	433	
Melt Point, TEP	°C	>257	ASTM E-794
Yield	ft ² /lb	78	-
	m ² /kg	16	
Density	g/cc	1.65	ASTM D-1505

Results Below - polyimide film data only


Dielectric Constant @ 1 kHz	-	3.4	ASTM D-150
Dissipation Factor @ 1 kHz	-	0.002	ASTM D-150
Volume Resistivity	ohm-cm	>10 ¹⁶	ASTM D-257
UL Electrical RTI	°C	240*	UL 746B
UL Mechanical RTI	°C	200*	UL 746B
Flammability	UL-94	V-0*	UL Test Method

*Expected results at UL, material under current review

DUPONT™ KAPTON® 150FCRC019

TECHNICAL DATA SHEET

FIGURE 1—COMPARISON OF VOLTAGE ENDURANCE, DUPONT™ KAPTON® CORONA RESISTANT BASE FILM (100CRC) TO DUPONT™ KAPTON® 100HN



For more information on DuPont™ Kapton® polyimide films, please contact your local representative, or visit our website for additional regional contacts:

Americas

DuPont High Performance Films
U.S. Rt. 23 & DuPont Road
Circleville, OH 43113
Tel: 800-967-5607

Asia

DuPont Taiwan
No. 45, Hsing-Pont Road
Taoyuan, Taiwan, R.O.C.
Tel: 886-3-377-3688

Japan

DuPont-Toray Co., Ltd.
5-6 Nihonbashi Honcho 1-chome
Chuo-ku, Tokyo 103-0023 Japan
Tel: 81-3-3245-5061

Europe

DuPont de Nemours (Luxembourg) S.A.R.L.
Rue General Patton
L-2984 Luxembourg
Tel: 352-3666-5935

DuPont Shanghai
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai,
P.R. China 201203
Tel: 86-21-3862-2888

kapton.dupont.com

Copyright © 2014 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and all DuPont products denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-4.