

PRODUCT INFORMATION

THE UL YELLOW CARD

The UL Yellow Card displays the key information for UL Recognized materials, based on testing according to UL Standards. The following tables show this information

for NOMEX® brand paper and pressboard products when tested per the noted Standard. Areas in the tables with no data have not been tested.

Type 410 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
2	0.05		0	4	220	220	3	3
3	0.08		0	4	220	220	3	3
5	0.13	V-0	0	4	220	220	3	3
7	0.18	V-0	0	4	220	220	3	3
10	0.25	V-0	0		220	220	3	3
12	0.30	V-0	0		220	220	3	3
15	0.38	V-0	0	0	220	220	3	3
20	0.51	V-0	0	0	220	220	3	3
24	0.61	V-0	0	0	220	220	3	3
29	0.74	V-0	0	0	220	220	3	3
30	0.76	V-0	0	0	220	220	3	3

Type 411 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
5	0.13		0	4	220	220	1	3
7	0.18	V-0	0	4	220	220	1	3
10	0.25	V-0	0	4	220	220	1	3
15	0.38	V-0	0	0	220	220	1	3
23	0.58	V-0	0	0	220	220	1	3

Type 414 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
3.4	0.09		0		220	220	3	3
7	0.18	V-0	0	0	220	220	3	3
10	0.25	V-0	0	0	220	220	3	3
12	0.30	V-0	0	0	220	220	3	3
15	0.38	V-0	0	0	220	220	3	3

Type 418 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
3	0.08	V-0	4	4	220	220	3	3
5	0.13	V-0	4	4	220	220	3	3
8	0.20	V-0	4	4	220	220	3	3
10	0.25	V-0	4	4	220	220	3	3
14	0.36	V-0	4	4	220	220	3	3

Type 419 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
7	0.18	V-0		3	220	220	2	
13	0.33	V-0	4	4	220	220	2	

Type E56 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
5	0.13	VTM-0	0		220	220		3
7	0.18	V-0	0		220	220		3
10	0.25	V-0	0		220	220		3
12	0.30	V-0	0		220	220		3
15	0.38	V-0	0	3	220	220		3
20	0.51	V-0	0	3	220	220		3

Type 992 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
63	1.6	V-0	1		220	220	3	3
125	3.2	V-0	0		220	220	3	3

Type 993 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
40	1.0	V-0	3		220	220	2	3
60	1.5	V-0			220	220	2	3
80	2.0	V-0			220	220	2	3
95	2.4	V-0			220	220	2	3
120	3.0	V-0	0		220	220	2	3
160	4.0	V-0	0		220	220	2	3

Type 994 UL Ratings

ASTM D374 Thickness (mils)	ASTM D374 Thickness (mm)	UL 94 Flame Class	UL746A HWI Rating	UL746A HAI Rating	UL746B RTI Elec. Rating	UL746B RTI Mech. Rating	UL746A HVTR Rating	UL746A CTI Rating
40	1.0	V-0			220	220	2	3
60	1.5	V-0			220	220	2	3
80	2.0	V-0	1		220	220	2	3
120	3.0	V-0	1		220	220	2	3
125	3.2	V-0	1		220	220	2	3
160	4.0	V-0	1		220	220	2	3
190	4.8	V-0	1		220	220	2	3
200	5.0	V-0	1		220	220	2	3
240	6.0	V-0	1		220	220	2	3
250	6.4	V-0	1		220	220	2	3
275	7.0	V-0	1		220	220	2	3
315	8.0	V-0	1		220	220	2	3
380	9.6	V-0	1		220	220	2	3

UL 94 Flame Class – UL94 Flammability Classification

UL94 refers to the testing methods used to rate different plastics according to the ease of extinguishment after the ignition flame has been removed. Materials are classified as 94V-0, 94V-1, 94V-2, 94VTM-0, 94VTM-1, 94VTM-2, 94HF-1, 94HF-2, 94HBF, 94HB, 94-5VA, and 94-5VB.

RTI Elec – Relative Temperature Index, Electrical Properties

Shows the hot spot temperature in °C at which after 100,000 hours (11.4 years) the most sensitive electrical property drops to 50% of its initial value.

RTI Mech – Relative Temperature Index, Mechanical Properties Without Impact

Shows the hot spot temperature in °C at which after 100,000 hours (11.4 years) the most sensitive non-impact related mechanical property drops to 50% of its initial value.

HWI – Hot Wire Ignition

Judges the ease of ignition of a material in contact with a heat source (not an open flame). Performance is expressed as the mean number of seconds needed either to ignite the standard specimens or to burn through the specimens without ignition.

Mean Ignition Time (IT in sec)	Rating
120 IT	0
60 IT < 120	1
30 IT < 60	2
15 IT < 30	3
7 IT < 15	4
0 IT < 7	5

HAI – High Amperage Arc Ignition

This test simulates the situation when an arc occurs between two electrodes under low voltage but a high current. Performance is expressed as the number of arc rupture exposures which are necessary to ignite the material when they are applied at a standard rate, either on the surface of the material or at a specified distance from it.

Mean Number of Arcs to Cause Ignition (NA)	Rating
120 NA	0
60 NA < 120	1
30 NA < 60	2
15 NA < 30	3
0 NA < 15	4

HVTR – High Voltage Arc Tracking Rate

This test is designed to determine the ability of a material to withstand repeated high-voltage low-current arcing at its surface without forming a conductive path. Performance is expressed as the rate (mm/minute) at which a tracking path can be produced on the surface of the material under standardized test conditions.

Tracking Rate (TR in mm/min.)	Rating
0 < TR 10	0
10 < TR 25.4	1
25.4 < TR 80	2
80 < TR 150	3
150 < TR	4

CTI – Comparative Tracking Index

This test simulates the case when a current develops due to surface contamination of the plastic insulators in between two conductors. Performance is expressed as that voltage which causes tracking on a material after 50 drops of 0.1% ammonium chloride solution have fallen.

Tracking Index (TI in volts)	Rating
600 TI	0
400 TI < 600	1
250 TI < 400	2
175 TI < 250	3
100 TI < 175	4
0 TI < 100	5

USA

DuPont
Advanced Fibers Systems
Customer Inquiry Center
5401 Jefferson Davis Highway
Richmond, VA 23234
Tel: (800) 453-8527
(804) 383-4400
Fax: (800) 787-7086
(804) 383-4132
E-mail: afscdt@usa.dupont.com

CANADA

DuPont Canada, Inc.
Advanced Fibers Systems
P.O. Box 2200
Streetsville Postal Station
Mississauga, Ontario, L5M 2H3
Canada
Tel: (800) 387-2122
(905) 821-5193
Fax: (905) 821-5177
E-mail: products@can.dupont.com

EUROPE

Du Pont de Nemours International S.A.
Advanced Fibers Systems
P.O. Box 50
CH-1218 Le Gran-Saconnex
Geneva, Switzerland
Tel: +41-22-717-5111
Fax: +41-22-717-6218
E-mail: info.nomex@che.dupont.com

SOUTH AMERICA

DuPont do Brasil S.A.
Alameda Itapecuru, 506
BR-06454-080 Alphaville
Barueri, São Paulo, Brasil
Tel: +0800-17-17-15
+55 11 4166 8449
Fax: +55 11 7266 8904
E-mail: produtos.brasil@bra.dupont.com

JAPAN

DuPont Teijin Advanced Papers (Japan) Limited
ARCO Tower,
8-1 Shimomoguro I-chome
Meguro-ku, Tokyo 153-0064
Japan
Tel: +81-3-5434-6609
Fax: +81-3-5434-6605
E-mail: chihiro.kondo@jpn.dupont.com

ASIA PACIFIC

DuPont Teijin Advanced Papers (Asia) Limited
1122 New World Office Building, East Wing
24 Salisbury Road
Tsimshatsui, Kowloon
Hong Kong
Tel: +852-2734-5363
Fax: +852-2734-5486
E-mail: nomexpaper@hkg.dupont.com

www.dupont.com/nomex

Product safety information is available upon request.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experiments. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DUPONT MAKES NO WARRANTIES AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

© Copyright 2003 E.I. du Pont de Nemours and Company.
All rights reserved. The DuPont oval logo, The miracles of science®, DuPont™, and NOMEX® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company.

H-93498-12 Rev. 04/03 Printed in USA



The miracles of science®