

Specification Properties of Legacy Tyvek® 1073B and 1059B

English

Property	Comparable Standard Test Method	Units	Nominal Value [range]	
			Legacy Tyvek® 1073B	Legacy Tyvek® 1059B
Basis Weight	ASTM D3776 ¹ EN ISO 536 ¹	oz/yd ²	2.20 [2.10–2.30]	1.90 [1.82–1.98]
Delamination	ASTM D2724 ²	lb _f	0.5 [0.4–0.7]	0.5 [0.3–0.7]
Gurley Hill Porosity	TAPPI T460 ¹ ISO 5636-5 ³	sec/100 cc	22 [8–36]	20 [8–36]

Metric

Property	Comparable Standard Test Method	Units	Nominal Value [range]	
			Legacy Tyvek® 1073B	Legacy Tyvek® 1059B
Basis Weight	ASTM D3776 ¹ EN ISO 536 ¹	g/m ²	74.6 [71.2–78.0]	64.4 [61.7–67.1]
Delamination	ASTM D2724 ²	N	2.3 [1.6–3.1]	2.2 [1.5–2.9]
Gurley Hill Porosity	TAPPI T460 ¹ ISO 5636-5 ³	sec/100 cc	22 [8–36]	20 [8–36]

NOTES: Specification properties are controlled to a nominal value and released within specifications. The customer is responsible for determining that Legacy Tyvek® is suitable for the intended application. The ranges represent the controlled minimum and maximum values in which the product is released. Specification properties are based on roll averages, with samples taken uniformly across the sheet. These properties are representative for uncoated Legacy Tyvek® as sold by DuPont. Any downstream operations, such as coatings applied by sterile packaging manufacturers (SPMs), may change these values.

1. Modified sample size.
2. Modified for speed, sample width (2.54 cm/1 in.) and gauge length.
3. Modified for sealing fluid characteristics.

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, DUPONT MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUMES NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™ and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. (o6/17)