

Adhesion Performance Comparison Table for DuPont™ Bynel® Resins

TYPICAL ADHESION PERFORMANCE IN A MELT COEXTRUSION

Legend:

[0] = Standard Performance

[+] = High Performance

Notes:

1.) resin is intended to be used in blending and not pure

2.) resin may be used pure or in blends

3.) see below for explanation

Grade	Notes	Melt Flow	Melt Point (deg. C)	Vicat Point (deg. C)	FDA (21 CFR xxx)	EVOH (long) (See note 3)	EVOH (short) (See note 3)	Polyamide (nylon)	Polyethylene	Polypropylene	Polystyrene	Polyester	Ionomer
Series 1100 - Modified Ethylene Vinyl Acetate													
Bynel® 1123		6.7	74	50	177.1350			[0]	[+]	[0]	[0]	[0]	[+]
Bynel® 1124		25	70	49	177.1350			[0]	[+]	[0]	[0]	[0]	[+]
Series 2000 - Acid Modified Ethylene Acrylate													
Bynel® 2002		10	91	60	177.1330(b)			[+]	[0]				[+]
Bynel® 2022		35	87	58	177.1330(b)			[+]	[0]				[+]
Series 2100 - Anhydride Modified Ethylene Acrylate													
Bynel® 21E533		7.7	83	50	175.105	[+]	[+]	[+]	[+]	[0]	[0]	[+]	[+]
Bynel® 21E781		2	97		175.105	[+]	[+]	[+]	[+]				[+]
Bynel® 21E810		1.9	94	57	175.105	[0]	[0]	[+]	[+]	[0]		[+]	[+]
Bynel® 21E830		5	93		175.105	[0]	[0]	[+]	[+]	[0]		[+]	[+]
Series 2200 - Modified Ethylene Acrylate													
Bynel® 22E757		8	92	54	177.1340				[+]	[0]		[+]	[0]
Bynel® 22E780		2	91	48	177.1340				[+]	[0]		[+]	[0]
Bynel® 22E804		5	93	51	177.1340				[+]	[0]		[+]	[0]



The miracles of science™



Grade	Notes	Melt Flow	Melt Point (deg. C)	Vicat Point (deg. C)	FDA (21 CFR xxx)	EVOH (long) (Note 3)	EVOH (short) (Note 3)	Polyamide (nylon)	Polyethylene	Polypropylene	Polystyrene	Polyester	Ionomer
-------	-------	-----------	---------------------	----------------------	------------------	----------------------	-----------------------	-------------------	--------------	---------------	-------------	-----------	---------

Series 3000 - Anhydride Modified Ethylene Vinyl Acetate

Bynel® 30E670		0.8	96	84	175.105			[+]	[+]				[0]
Bynel® 30E671		2.1	99	81	175.105			[+]	[+]				[0]
Bynel® 30E753		2.1	92	65	175.105				[+]				
Bynel® 30E783		5.7	92	67	175.105			[+]	[+]				[0]

Series 3100 - Acid / Acrylate Modified Ethylene Vinyl Acetate

Bynel® 3101		3.2	87	65	175.1350			[0]	[+]	[0]	[0]	[0]	[+]
Bynel® 3126		8.1	87	60	175.1350			[0]	[+]	[0]	[0]	[0]	[+]

Series 3800 - Anhydride Modified Ethylene Vinyl Acetate

Bynel® E418		10.9	74	42	175.105	[0]	[0]	[+]	[0]	[0]	[+]	[+]	[+]
Bynel® 3810		2.6	75	49	175.105	[0]	[0]	[+]	[0]	[0]	[+]	[0]	[0]
Bynel® 3859		4.3	76	62	175.105	[0]	[0]	[+]	[0]	[0]	[+]	[0]	[0]
Bynel® 3860		5.7	74	48	175.105	[0]	[0]	[+]	[0]	[0]	[0]	[0]	[+]
Bynel® 3861		2	80	56	175.105	[0]	[0]	[+]	[0]	[0]	[0]	[0]	[+]

Series 3900 - Anhydride Modified Ethylene Vinyl Acetate

Bynel® 3930		0.85	99	82	177.1350 / 175.105	[0]	[0]	[+]	[+]				[0]
Bynel® 39E660		2.9	95	72	177.1350 / 175.105			[+]	[+]	[0]	[0]	[0]	[0]

Series 4000 - Anhydride Modified High Density Polyethylene

Bynel® 4033	1)	2	135	128	175.105	[+]	[+]	[+]	[+]				
Bynel® 40E529		3.5	135	119	175.105	[+]	[0]	[+]	[+]				



Grade	Notes	Melt Flow	Melt Point (deg. C)	Vicat Point (deg. C)	FDA (21 CFR xxx)	EVOH (long) (Note 3)	EVOH (short) (Note 3)	Polyamide (nylon)	Polyethylene	Polypropylene	Polystyrene	Polyester	lonomer
-------	-------	-----------	---------------------	----------------------	------------------	----------------------	-----------------------	-------------------	--------------	---------------	-------------	-----------	---------

Series 4100 - Anhydride Modified Linear Low Density Polyethylene

Bynel® 4104		1.1	125	110	175.105	[+]	[0]	[+]	[+]				[0]
Bynel® 4105		4	125	105	175.105	[+]	[0]	[+]	[+]				[0]
Bynel® 4109		3.1	126	87	175.105	[+]	[+]	[+]	[+]				[+]
Bynel® 4125		2.5	126	109	175.105	[+]	[0]	[+]	[+]				[0]
Bynel® 4140	1)	1.5	121	102	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 4157		3	127	93	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 4164	2)	1.2	127	110	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 41E556		3.4	126	105	175.105	[+]	[0]	[+]	[+]				[0]
Bynel® 41E687		1.7	119	84	175.105	[+]	[+]	[+]	[+]				[+]
Bynel® 41E710	1)	2.7	115	103	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 41E754		0.9	126	101	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 41E755		4.2	125	100	175.105			[+]	[+]				
Bynel® 41E762		2.5	127	100	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 41E766		2.2	121	91	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 41E850		1	120	88	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 41E865		4.1	111	100	175.105	[+]	[+]	[+]	[+]		[+]		
Bynel® 41E871	2)	1.9	121	100	175.105	[+]	[+]	[+]	[+]				

Series 4200 - Anhydride Modified Low Density Polyethylene

Bynel® 4206		2.5	102	75	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 4208		0.4	108	86	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 4288		4.7	104	86	175.105	[+]	[+]	[+]	[+]				[0]
Bynel® 42E703		6.4	105	80	175.105	[+]	[+]	[+]	[+]				[0]



Grade	Notes	Melt Flow	Melt Point (deg. C)	Vicat Point (deg. C)	FDA (21 CFR xxx)	EVOH (long) (Note 3)	EVOH (short) (Note 3)	Polyamide (nylon)	Polyethylene	Polypropylene	Polystyrene	Polyester	Ionomer
-------	-------	-----------	---------------------	----------------------	------------------	----------------------	-----------------------	-------------------	--------------	---------------	-------------	-----------	---------

Series 5000 - Anhydride Modified Polypropylene

Bynel@ 50E571		3.5	156	125	175.105	[+]	[0]	[+]		[+]			
Bynel@ 50E662		4	150	130	175.105	[+]	[0]	[+]		[+]			
Bynel@ 50E725		3	144	114	175.105	[+]	[+]	[+]		[+]			
Bynel@ 50E739		6	142	107	175.105	[+]	[+]	[+]		[+]			
Bynel@ 50E803	1)	470	135	112	175.105	[+]	[+]	[+]		[+]			
Bynel@ 50E806	2)	25	140	100	175.105	[+]	[+]	[+]		[+]			

NOTE 3)		
EVOH Processing Time	Relative "extrusion processing time" for coextrusion adhesion generation	L = Long process time S = Short process time
Primary Process	Secondary Process	Process Time Type
Blown Film (standard)		S or L (design dependent)
Blown Film (water quench)		S
Cast Film		S
Coextrusion Coating / Laminating		S
Sheet Extrusion		L
Sheet Extrusion	Melt Phase Thermoforming	L
Sheet Extrusion	Solid Phase Thermoforming	S
Tubing		L
Extrusion Blow Molding		L

Sales and Technical Support Locations

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

Americas

DuPont Company, BMP26-2215
Lancaster Pike & Route 141 Americas
Wilmington, DE 19805 U.S.A.
Telephone +1 302 774 1161
Toll-free (USA) 800 628 6208, ext. 6
Fax +1 302 355-4056

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone +55 11 4166 8000

Fax +55 11 4166 8736

Asia Pacific

DuPont China Holding Co., Ltd.
Shanghai Branch
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai
P.R. China (Postcode: 201203)
Telephone +86-21-3862-2888
Fax +86-21-3862-2889

Europe, Middle East, Africa

DuPont de Nemours Int'l. S.A.
2, Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

contact us: bynel.dupont.com

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

CAUTION: This product is not permitted to be sold for use in medical applications involving any implantation in the human body or where contact with internal body fluids or tissues will equal or exceed 24 hours. For applications involving contact of less than 24 hours, see "DuPont Medical Caution Statement" H-50102 or contact your DuPont sales representative.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and Bynel® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

K-22059 (03/09) Printed in the U.S.A.



The miracles of science™