

DuPont™ Appeel® 11D888

Appeel® resins Product Data Sheet

Description

| | |
|---------------------|--|
| Product Description | <p>Appeel®11D888 is a developmental modified ethylene vinyl acetate resin designed to function as a sealing layer for lidding applications. It is most often suggested to provide peelable seals over a broad temperature range to containers constructed of PP, PS & PET. Appeel® 11D888 is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene resins.</p> |
|---------------------|--|

Restrictions

| | |
|-----------------|---|
| Material Status | <ul style="list-style-type: none"> • Developmental: Active |
|-----------------|---|

Typical Characteristics

| | |
|----------------------------|---|
| Uses | <ul style="list-style-type: none"> • Lidding Sealant |
| Characteristics / Benefits | <p>Appeel® 11D888 provides low temperature heat seal initiation and easy peel characteristics to a variety of substrates.</p> |
| Applications | <p>Lidding sealant providing easy opening.</p> |

Typical Properties

| Physical | Nominal Values | Test Method(s) | |
|---------------------------------|------------------------|----------------|----------|
| * Density () | 0.94 g/cm ³ | ASTM D792 | ISO 1183 |
| * Melt Flow Rate (190°C/2.16kg) | 32 g/10 min | ASTM D1238 | ISO 1133 |

| Thermal | Nominal Values | Test Method(s) | |
|---------------------------|----------------|----------------|----------|
| * Melting Point (DSC) | 71°C (160°F) | ASTM D3418 | ISO 3146 |
| Vicat Softening Point () | 55°C (131°F) | ASTM D1525 | ISO 306 |

Heat Seal Evaluation

The performance of any sealant resin should be evaluated within the context of the application. The sealant is designed to bond to particular substrate(s). Many variables can affect seal strength, including the physical properties of the substrate being sealed to, thickness, flange or surface design, heat seal temperature, dwell time and pressure. The condition and type of the sealing equipment used, such as roller sealers versus platen seal mechanisms can make a significant difference.

In most cases sealant peel strength is used as a measure of performance. Although this is a convenient test, peel strength is affected not only by substrate adhesion but also by peel angle, separation rate, ambient temperature, tensile and modulus properties of the materials, and often by the time elapsed since the formation of the bond.

If sealant peel strength is used as a measure of sealant performance, it is imperative that peel strength be evaluated not only at the time of initial heat sealing the lid to the

substrate, but throughout the life of the product and under all the conditions to which the sealant will be exposed. Only then does peel strength provide a reliable indication of adhesive performance in the specific application.

Processing Information

General

- * Maximum Processing Temperature 235°C (455°F)

Extrusion Coating/Lamination Processing

Nominal Values

Extrusion Coating / Lamination Processing

Extrusion Coating: The melt temperature of Appeel® 11D888 should be maintained in the 210°- 235°C (410°- 455°F) range in extrusion coating processes. Selection of a specific melt temperature will depend on screw configuration, potential power limitations, and the need to match melt viscosities. However, melt temperatures above 235°C (455°F) should be avoided because of possible thermal degradation of the resin.

After processing Appeel®, purge the materials out using a polyethylene resin, preferably with a lower melt flow rate than the Appeel® resin in use, and at the temperatures used to process this resin.

Do not raise the extrusion system temperatures above these settings until all the Appeel® resin is fully purged.

The "Disco Purge Method" is suggested as the preferred purging method, as this method usually results in a more effective purging process. Information on the Disco Purge Method can be obtained via your DuPont Sales Representative.

Never shut down the extrusion system with Appeel® in the extruder and die. Properly purge out the Appeel® with polyethylene, and shut down the line with polyethylene or polypropylene in the system.

Following is a suggestion for an initial processing profile for Appeel® 11D888. The processing parameters can then be tailored to your extrusion needs. But avoid melt conditions hotter than 235C.

| | |
|--------------|---------------|
| Feed Zone | 140°C (284°F) |
| Second Zone | 190°C (374°F) |
| Third Zone | 210°C (410°F) |
| Fourth Zone | 220°C (428°F) |
| Fifth Zone | 220°C (428°F) |
| Adapter Zone | 220°C (428°F) |
| Die Zone | 220°C (428°F) |

FDA Status Information

Appeel® 11D888 complies with Food and Drug Administration Regulation 21 CFR 177.1350(a)(1) --Ethylene -vinyl acetate copolymers, subject to the limitations and requirements therein. This Regulation describes polymers that may be used in contact with food, subject to the finished food-contact article meeting the extractive limitations under the intended conditions of use, as shown in paragraph (b)(1) of the Regulation

The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by DuPont and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, DuPont cannot guarantee or warrant such certifications or information and assumes no liability for their use.

Regulatory Information

In Europe a diversity of regulations apply in various countries. In addition, constant changes linked to the effort of their harmonization under the umbrella of European Union Directive can be observed. This makes it impossible to accurately describe the food contact status in this brochure. Updated statements describing the situation in the

various European countries can be obtained through your local sales representative.

Safety & Handling

For information on appropriate Handling & Storage of this polymeric resin, please refer to the Material Safety Data Sheet..

A Product Safety Bulletin, Material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your DuPont Packaging and Industrial Polymers representative.

Read and Understand the Material Safety Data Sheet (MSDS) before using this product

Regional Centres

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

Americas

DuPont Company
Chestnut Run Plaza – Bldg. 730
974 Centre Road
Wilmington, Delaware
19805 U.S.A.
Toll-Free (USA): 1-800-628-6208
Telephone: 1-302-774-1000
Fax: 1-302-355-4013

Asia Pacific

DuPont China Holding Co., Ltd.
Shanghai Branch
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai
P.R. China (Postcode: 201203)
Telephone +86 21 3862 2888
Fax +86-21-3862-2889

Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.
2,Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone: +55 11 4166 8000
Fax: +55 11 4166 8736

<http://appeel.dupont.com>

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

This data sheet is effective as of 08/07/2010 02:00:11 PM and supersedes all previous versions.