

DuPont™ Biomax® Strong 120

Biomax® Strong resins Product Data Sheet

Description

Product Description

Biomax® Strong 120 is an ethylene copolymer designed to modify Polylactic Acid (PLA) for improved toughness properties in packaging and industrial applications. Some of the attributes of Biomax® Strong 120 in PLA include:

- Special Chemistry for PLA. Even small amounts provide toughness benefits;
- Engineered for PLA, rapid melt-dispersion, even with single screw extruders;
- Pelletized, efficient extruder feeding; separately or as a pellet-bend with PLA;

Blends containing 5% (wt.) or less modifier maintain contact clarity similar to clarified Polypropylene (PP), while blends in the 5% to 15% range presents different degrees of translucence, similar to unclarified PP.

Biomax® Strong 120 is similar to Biomax® Strong 100 but is designed for food packaging applications subject to the regulatory requirements detailed below.

Restrictions

Material Status

- Commercial: Active

Availability

- Globally

Typical Characteristics

Uses

- Plastics Modification

Characteristics / Benefits

Impact Strength / Toughness

Impact strength of BIOMAX® Strong 120 modified PLA, both in the amorphous and crystalline estates, is significantly improved even at 2wt% addition level.

Brittleness

BIOMAX® Strong 120 greatly improves the cutting & trimming of PLA 3001 & 2002. While unmodified PLA 3001 & 2002 exhibits breakage at the edge of the sheet, blends with 2 to 5 wt.% of BIOMAX® Strong 120 show no breakage. There is also a marked improvement of “pinning”. While unmodified PLA 3001 breaks at the edge of the sheet, there is no breakage once BIOMAX® Strong 120 is added.

Applications

Polylactic Acid (PLA) Modification

Typical Properties

Physical

Nominal Values

Test Method(s)

* Density ()

0.94 g/cm³

ASTM D792

ISO 1183

* Melt Flow Rate (190°C/2.16kg)	12 g/10 min	ASTM D1238	ISO 1133
Thermal	Nominal Values	Test Method(s)	
* Melting Point (DSC)	72°C (162°F)	ASTM D3418	ISO 3146

Attach Images Here

Processing Information

General

* Maximum Processing Temperature	280°C (536°F)
General Processing Information	Handling & Storage

Biomax® Strong 120 is supplied in polyethylene bag lined boxes or bags. The product does not require drying but the material should be handled in a way that minimizes moisture pick-up. For example reseal bags or box liners when partial bags or boxes are not being used.

Processing of blends of Biomax® Strong 120 and PLA

Blends of Biomax® Strong 120 and PLA can be processed in the same equipment and under the same processing conditions recommended for PLA

The melting point of Biomax® Strong 120 is 72C (162F) so a split feed extruder hopper will be required in cases where the PLA resin is dried on line and temperature of the hot dried PLA exceeds the melting point of the modifier.

Melt Viscosity and Melt Thermal Stability

Under typical processing conditions melt viscosity of PLA melt blends with Biomax® Strong 120 is not significantly different from that of unmodified PLA.

Melt Thermal stability of PLA is improved through addition BIOMAX® Strong 120 as it has been shown by extended hold-up time (up to two hours) in a capillary viscometer.

FDA Status Information

Biomax® Strong 120 resin modifier complies with U.S. Food and Drug Administration Regulation CFR 175.105 -- Adhesives. This Regulation describes adhesives that may be used as components of articles intended for use in packaging, transporting or holding food, subject to the limitations and requirements therein.

Biomax® Strong 120 resin modifier may be used at up to a level of 10% in polylactic acid (PLA) resin for direct food contact. The PLA resin containing Biomax® Strong 120 resin modifier is intended for contact with all food types under temperature conditions as severe as Condition of Use C as described in Table 2 of 21 CFR 176.170(c). Such use may be properly said to comply fully with the Federal Food, Drug and Cosmetic Act and all applicable food additive regulations.

Regulatory Information

For information on the compliance of Biomax® Strong 120 with food contact regulations outside the U.S., please consult your local DuPont representative.

Safety & Handling

For information on appropriate Handling & Storage of this polymeric resin, please refer to the Material Safety Data Sheet..

A Product Safety Bulletin, Material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your DuPont Packaging and Industrial Polymers representative.

Read and Understand the Material Safety Data Sheet (MSDS) before using this product

Regional Centres

DuPont operates in more than 70 countries. For help finding a local representative, please contact one of the following regional customer contact centers:

Americas

DuPont Company
Chestnut Run Plaza – Bldg. 730
974 Centre Road
Wilmington, Delaware
19805 U.S.A.
Toll-Free (USA): 1-800-628-6208
Telephone: 1-302-774-1000
Fax: 1-302-355-4013

Asia Pacific

DuPont China Holding Co., Ltd.
Shanghai Branch
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai
P.R. China (Postcode: 201203)
Telephone +86 21 3862 2888
Fax +86-21-3862-2889

Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.
2, Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone: +55 11 4166 8000
Fax: +55 11 4166 8736

<http://biomax.dupont.com>

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

This data sheet is effective as of 08/07/2010 02:20:06 PM and supersedes all previous versions.

2 attachments



food approval EU Biomax Strong 120.pdf



BIOMAX_Strong_120_FDA_Status_v1_en.pdf