

DuPont™ Selar® PA 2072

Selar® resins Product Data Sheet

Description

Product Description Selar® PA 2072 is an amorphous nylon (polyamide) resin which exhibits superior transparency, good barrier properties to gases, water, solvents and essential oils and high temperature structural properties which make it suitable for consideration in a number of applications.

It is available in the form of small, free flowing pellets in 25 kg (55 lb.) foil-lined bags or 750 kg. (1653 lb.) foil lined boxes.

Restrictions

Material Status Commercial: Active

Typical Characteristics

Composition 100% By Weight 6I/6T polyamide

Features Selar® PA 2072 barrier resin can be utilized in both flexible and rigid packaging structures and is characterized by very good gas O₂, CO₂ and moisture barrier. Furthermore, Selar® PA is unique in that its gas barrier improves with increasing relative humidity. It has excellent physical properties, high temperature resistance and excellent optical properties desirable in a structural resin. Like other nylons, Selar® PA barrier resin is an excellent barrier for many types of solvent systems. In general it has good resistance to aliphatic, aromatic hydrocarbons, dilute alkalis, higher molecular weight alcohols, and low concentrations of lower molecular weight alcohols. It is not recommended for acids or concentrated lower molecular weight alcohols. End use testing is recommended for each application. With its high degree of stiffness, very good gas and moisture barrier, solvent resistance and excellent gloss and clarity, Selar® PA used in monolayer provides a "glass like" container for rigid packaging.

Characteristics / Benefits "Inherent Viscosity" of 0.72 via ASTM D4066
 "Moisture content" at time of packaging: --- max 0.05 % via ISO 15512

Applications Modification of EVOH for broader thermoforming window.

Nylon 6 modification for better oxygen barrier (at higher humidities), broader thermoforming window, and easier extrusion processing,

Typical Properties

Physical	Nominal Values	Test Method(s)	
*Density ()	1.19 g/cm ³	ASTM D792	ISO 1183
*Solution Viscosity ()	*** See IV information above ***		
Thermal	Nominal Values	Test Method(s)	
*Glass Transition Temperature (DSC)	125 °C (257 °F)	ASTM D3417	ISO 3146

Processing Information

***Maximum Processing Temperature** 310 °C (590 °F)

General Processing Information DuPont™ Selar® PA is an amorphous nylon resin which can be processed on conventional extrusion, coextrusion, injection Molding or blow molding equipment that is designed to process nylon or polyolefin resins.

Suggested "start-up" melt temperatures should be in the minimum range of 240°C to 250°C (464°F to 482°F) unless prior experience has shown that lower temperatures are acceptable. If lower melt temperatures are desired, machine temperatures should be reduced after "start-up" while carefully monitoring drive power and head pressure.

FDA Status Information

SELAR® PA 2072 Barrier Resin complies with Food and Drug Administration Regulation 21 CFR 177.1500(a)(12) and (b)(12) - - Nylon resins, subject to the limitations and requirements therein. This Regulation describes nylon resins that may be used in contact with food, except alcoholic beverages containing more than 8 percent alcohol.

The information and certifications provided herein are based on data we believe to be reliable, to the best of our knowledge. The information and certifications apply only to the specific material designated herein as sold by DuPont and do not apply to use in any process or in combination with any other material. They are provided at the request of and without charge to our customers. Accordingly, DuPont cannot guarantee or warrant such certifications or information and assumes no liability for their use.

Regulatory Information

For information on regulatory compliance outside of the U.S., consult your local DuPont representative.

Safety & Handling

For information on appropriate Handling & Storage of this polymeric resin, please refer to the material Safety Data Sheet..

A Product Safety Bulletin, material Safety Data Sheet, and/or more detailed information on extrusion processing and/or compounding of this polymeric resin for specific applications are available from your DuPont Performance Materials representative.

Regional Centres

DuPont operates in more than 70 countries.

For help finding a local representative, please contact one of the following regional customer contact centers:

Americas

DuPont Company
Chestnut Run Plaza – Bldg. 730
974 Centre Road
Wilmington, Delaware
19805 U.S.A.
Toll-Free (USA): 1-800-628-6208
Telephone: 1-302-774-1000
Fax: 1-302-355-4013

DuPont do Brasil, S.A.
Alameda Itapecuru, 506
06454-080 Barueri, SP Brasil
Telephone: +55 11 4166 8000
Fax: +55 11 4166 8736

Asia Pacific

DuPont China Holding Co., Ltd.
Shanghai Branch
399 Keyuan Road, Bldg. 11
Zhangjiang Hi-Tech Park
Pudong New District, Shanghai
P.R. China (Postcode: 201203)
Telephone +86 21 3862 2888
Fax +86-21-3862-2889

Europe / Middle East / Africa

DuPont de Nemours Int'l. S.A.
2,Chemin du Pavillon Box 50
CH-1218 Le Grand Saconnex
Geneva, Switzerland
Telephone +41 22 717 51 11
Fax +41 22 717 55 00

<http://www.dupont.com>

The data listed here fall within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The DuPont Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a licence to operate under, or a recommendation to infringe, any patent of DuPont or others. Since DuPont cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information.

CAUTION: Do not use DuPont materials in medical applications involving implantations in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your applications and expressly acknowledges the contemplated use. For our DuPont representative You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications H-50102-3.

Copyright © 2009 DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, and trademarks designated with "®" are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved