


DuPont™ Kalrez® 9600

For High Temperature Semiconductor Applications
Involving Fluorine & Oxygen Plasma Radicals

Preliminary Technical Information – November, 2017

Product Description

DuPont™ Kalrez® 9600 perfluoroelastomer parts are designed for high purity, high temperature vacuum applications where seals are exposed to damaging Fluorine and Oxygen plasma radicals. In addition to its extremely low erosion rate and weight loss from plasma attack, this well balanced material provides excellent chemical resistance to Ammonia, Ozone, and Water Vapor. Its outstanding resilience in compression and ultra-low outgassing at high temperature conditions makes it especially suitable for applications where purity of the process environment is paramount, such as Plasma-Enhanced Atomic Layer Deposition and Chemical Vapor Deposition processes used in fabricating next generation semiconductor chips. A maximum application temperature of 315°C is suggested. Ultrapure cleaning and packaging are standard for all Kalrez® 9600 parts.



Performance Features and Benefits

- Exceptional thermal stability
- Outstanding erosion resistance to damaging Fluorine and Oxygen plasma radicals
- Ultra-low particle generation
- Excellent (low) compression set properties
- Superb seal force retention properties
- Ultra-low outgassing
- Increased tool uptime and yield
- Reduced total cost of ownership

Suggested Applications

- Gas and plasma delivery system seals
- Reaction chamber seals
- Bonded gate and slit valve seals
- Pendulum and isolation valve seals

Typical Physical Properties¹

Color	Olive-Green
Hardness, Shore A (Plied Slab) ²	70
100% Modulus ³ , MPa (psi)	4.76 (690)
Tensile Strength at Break ³ , MPa (psi)	13.43 (1948)
Elongation at Break ³ , %	218
Compression Set ⁴ , %	
70 h at 204°C (400°F)	15
70 h at 300°C (572°F)	43
Maximum Application Temperature ⁵ , °C (°F)	315 (600)

¹ Not to be used for specifications

² ASTM D2240 (plied slab test specimens)

³ ASTM D412 (dumbbell test specimens)


⁴ ASTM D395B and ASTM D1414 (AS568 K214 O-ring test specimens)

⁵ DuPont proprietary test method




The miracles of science™

Sealing Performance After Exposure to Fluorine & Oxygen Plasma Radicals¹



¹ DuPont proprietary test method

Sealing Performance At High Temperatures¹



¹ DuPont proprietary test method



The miracles of science™

Note: Color variations may be observed in DuPont™ Kalrez® 9600 parts. Variations are considered to be cosmetic. See below for additional details. Please contact a Kalrez® Application Engineer if you have any questions or if you need any additional information.

Marks (Dark Spots)

Small marks (dark spots) may be present in Kalrez® 9600 parts. The mark (dark spot) is a result of the curing process and is inherent in the part. It is not indicative of foreign matter and is not expected to have an adverse effect on the performance of the part in service.

Darker Sealing Element — Bonded Door Seal (BDS)

The color of the sealing element in a Kalrez® 9600 bonded door seal (BDS) is darker than a Kalrez® 9600 O-ring for two reasons:

- 1) Kalrez® 9600 BDS are manufactured at different standard operating conditions versus Kalrez® 9600 O-rings.
- 2) Since the sealing element is bonded to aluminum on at least one or more sides, less light passes through it. In both cases, this is a color issue, i.e., the darker color is not indicative of foreign material present in the sealing element nor is it expected to have an adverse effect on the performance of Kalrez® 9600 BDS in service.

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America

800-222-8377

Latin America

+0800 17 17 15

Europe, Middle East, Africa

+41 22 717 51 11

Greater China

+86-400-8851-888

ASEAN

+65-6586-3688

Japan

+81-3-5521-8484

The information provided in this data sheet corresponds to DuPont knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-5 and DuPont CAUTION Regarding Medical Applications H-50102-5.

Copyright © DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez® is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(06/04) Reference No. KZE-A40061-00-A1117



The miracles of science™