

DuPont™ Zytel® 3D12G30FL BK309

High Performance Material for 3D Printing

Developmental Data

Product Information

Zytel® 3D12G30FL BK309 is a 30% glass reinforced, heat stabilized long chain polyamide material in filament form for fused filament fabrication.

Material Specific Properties	Value	Unit	Test Standard
Density	1.29	g/cm ³	ISO 1183
Melting Temperature, 10°C/min	198	°C	ISO 11357-1/-3
Typical Properties of Printed Parts	Value	Unit	Test Standard
Tensile Stress at Break	75	MPa	ISO 527 (Type 1A)
Tensile Strain at Break	2.5	%	ISO 527 (Type 1A)
Tensile Modulus	4300	MPa	ISO 527 (Type 1A)
Izod Impact - Notched	18	kJ/m ²	ISO 180/1A
Izod Impact - Unnotched	41	kJ/m ²	ISO 180/1U
Deflection Temperature Under Load, 0.45MPa	159	°C	ISO 75

The above data are for developmental samples and are subject to change.

DuPont Zytel® 3D12G30FL BK309 is capable of being printed on a variety of printers in a variety of configurations. Different printers, slicing and/or printing configurations, test conditions, ambient environments, etc. may give different results.

Reported above are typical results obtained from test parts prepared from filament dried under vacuum at 80 - 90°C for 12 - 24 h. The printer settings were as follows: Nozzle Temperature: 275°C; Bed Temperature: 85°C; Printing Speed: 30 mm/sec; Cooling Fan: Off; Infill: 100% Diagonal Line; Flow: 100%; Retraction Speed: 10 mm/sec; Retraction Distance: 1 mm; Printing orientation: All test specimens were printed using Flat orientation except DTUL, which was Edge orientation.

Test specimens were stored under nitrogen and then vacuum-sealed in aluminum-lined bags prior to testing. The tests were then run at 23°C and 50% relative humidity on the dry-as-printed (DAP) test parts.

All information supplied by or on behalf of DuPont in relation to this product, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but the product is sold "as is". DuPont assumes no liability and makes no representations or warranties, express or implied, of merchantability, fitness for a particular purpose, or of any other nature with respect to information or the product to which information refers and nothing herein waives any of the seller's conditions of sale. Safety Data Sheets providing safety precautions that should be observed when handling and storing our products are available online or by request. You should obtain and review available material safety information before handling our products. The user assumes all responsibility for the use of any information provided and for the product.

Copyright © 2017 DuPont. The DuPont Oval Logo, DuPont™ and Zytel® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

Revised: 2019-01-07

To find out more, visit www.3DPrintingSolutions.DuPont.com or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11

