

Vizilon® Thermoplastic Composite Sheet

Vizilon® SU63G1-Series

Vizilon® SU63G1-Series is a heat-stabilized, 4-1 biased, plain-weave glass fabric-reinforced, polyamide-based thermoplastic composite sheet, available in widths up to 1,440 mm. It is optimized for heat-aging resistance and overmolding adhesion.

Vizilon® SU63G1-Series is suitable for structural parts where there is a need for both lightweighting and functional integration.

Mechanical properties were measured on 1.6 mm thick test coupons cut from original sheets.

Please note that mechanical properties in this data sheet are indicative of the product in original sheet form. Any subsequent processes applied to the sheet product may change its properties.

Property	Test method	Units	Warp direction	Weft direction
----------	-------------	-------	----------------	----------------

Vizilon® SU63G1-Series: Reinforcement

Fiber	-	-	Roving glass	
Fabric	-	-	4-1 biased, plain-weave	
Warp to weft ratio	-	%	80	20

Vizilon® SU63G1-Series: Sheet

Thickness available	-	mm	0.5 / 1.0 / 1.5 / 2.0 / 2.5			
Fiber mass fraction (M_f)	-	%	63			
Fiber volume fraction (V_f)	-	%	43			
Density	ISO 1183	g/cm ³	1.78			
Part Marking Code	ISO 11469	-	›PA-GF63‹			

Vizilon® SU63G1-Series: Thermal

Melting temperature	ISO 11357-1/-3	° C	260			
---------------------	----------------	-----	-----	--	--	--

Vizilon® SU63G1-Series: Mechanical

			DAM	50% RH	DAM	50% RH
Tensile modulus, 23° C	ISO 527-4	GPa	30	26	13	10
Tensile stress at break, 23° C	ISO 527-4	MPa	673	502	133	140
Tensile strain at break, 23° C	ISO 527-4	%	2.4	2.0	1.7	1.9



The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience become available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; it is not intended to substitute for any testing you may need to conduct to determine the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee favorable results, makes no warranties and assumes no liability in connection with any use of this information.

All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent. DuPont advises you to seek independent counsel for the freedom to practice opinion on the intended application or end-use of our products.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-5 and DuPont CAUTION Regarding Medical Applications H-50102-5.

For more information, visit www.vizilon.dupont.com