

# DUPONT™ TYVEK® 1079

## PRODUCT PROPERTIES—METRIC UNITS

**Product Features:**  
**Antistatic Treatment**  
**Corona Treated**  
**Calendered**

### Specification Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1079
Basis Weight	ASTM D3776	g/m <sup>2</sup>	96.6 [93.2–99.4]
Delamination	ASTM 2724 <sup>1</sup>	N/2.54 cm	3.2 [2.3–4.0]

Notes: Specification properties are based on roll averages from samples taken uniformly across the sheet. Specification properties are controlled to a nominal value and released within specification; the ranges listed represent the controlled minimum and maximum values in which the product is released. The customer is responsible for determining that Tyvek® is suitable for the intended application.

1. Modified for speed and sample width.

### Miscellaneous Properties (Metric Units)

Property	Comparable Test Method	Units	Tyvek® 1079
Thickness	ASTM D1777 <sup>1</sup> EN ISO 534 <sup>1</sup>	µm	211
Opacity	TAPPI T425 <sup>2</sup> ISO 2471 <sup>2</sup>	%	92
Elmendorf Tear, MD	ASTM D1424	N	3.3
Elmendorf Tear, CD	ASTM D1424	N	3.0
Tensile Strength, MD	ASTM D5035 <sup>3</sup> EN ISO 1924 <sup>3</sup>	N/2.54 cm	280
Tensile Strength, CD	ASTM D5035 <sup>3</sup> EN ISO 1924 <sup>3</sup>	N/2.54 cm	300

Notes: Miscellaneous properties are typical values based on roll averages from samples taken uniformly across the sheet. Miscellaneous properties are not controlled in the process; therefore, they are subject to slight change from normal process drift.

MD = machine direction; CD = cross direction.

1. Area = 2 cm<sup>2</sup>; pressure = 50 kPa

2. Modified for different backing standards, area, and illumination.

3. Modified for speed, sample width, and gauge length.

For more information about DuPont™ Tyvek®, call us today at 1.800.44.TYVEK

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark, or technical information of DuPont or others covering any material or its use.

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. K-29585 (4/17)

# DUPONT™ TYVEK® 1079

## PRODUCT PROPERTIES—ENGLISH UNITS

**Product Features:**  
**Antistatic Treatment**  
**Corona Treated**  
**Calendered**

### Specification Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1079
Basis Weight	ASTM D3776	oz/yd <sup>2</sup>	2.85 [2.75–2.93]
Delamination	ASTM 2724 <sup>1</sup>	lb <sub>f</sub> /inch	0.7 [0.5–0.9]

Notes: Specification properties are based on roll averages from samples taken uniformly across the sheet. Specification properties are controlled to a nominal value and released within specification; the ranges listed represent the controlled minimum and maximum values in which the product is released. The customer is responsible for determining that Tyvek® is suitable for the intended application.

1. Modified for speed and sample width.

### Miscellaneous Properties (English Units)

Property	Comparable Test Method	Units	Tyvek® 1079
Thickness	ASTM D1777 <sup>1</sup> EN ISO 534 <sup>1</sup>	mils	8.3
Opacity	TAPPI T425 <sup>2</sup> ISO 2471 <sup>2</sup>	%	92
Elmendorf Tear, MD	ASTM D1424	lb <sub>f</sub>	0.7
Elmendorf Tear, CD	ASTM D1424	lb <sub>f</sub>	0.6
Tensile Strength, MD	ASTM D5035 <sup>3</sup> EN ISO 1924 <sup>3</sup>	lb <sub>f</sub> /inch	62
Tensile Strength, CD	ASTM D5035 <sup>3</sup> EN ISO 1924 <sup>3</sup>	lb <sub>f</sub> /inch	68

Notes: Miscellaneous properties are typical values based on roll averages from samples taken uniformly across the sheet. Miscellaneous properties are not controlled in the process; therefore, they are subject to slight change from normal process drift.

MD = machine direction; CD = cross direction.

1. Area = 0.625 in<sup>2</sup>; pressure = 7.15 psi  
 2. Modified for different backing standards, area, and illumination.  
 3. Modified for speed, sample width, and gauge length.

For more information about DuPont™ Tyvek®, call us today at 1.800.44.TYVEK

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, WE MAKE NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATIONS, NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION.

This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark, or technical information of DuPont or others covering any material or its use.

Copyright © 2017 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and Tyvek® are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. K-29585 (4/17)