

DuPont™ Kapton® 100CRC

Product Description

DuPont™ Kapton® corona resistant film is a state of the art polyimide film that withstands the damaging effects of corona discharge. The corona resistance provides improved service life and operational efficiencies versus conventional insulation materials.

Kapton® 100CRC being a homogeneous film provides improved service life and operational efficiencies versus conventional insulation materials. In addition to the corona resistant properties, Kapton® CRC offers excellent, physical, electrical, thermal, and chemical resistant characteristics expected with Kapton® polyimide films.

Kapton® CRC polyimide film has been developed for use as an electrically insulating material for high voltage environments where the potential for corona discharge is present. Kapton® CRC is typically used in industrial motor and generator applications as magnet wire, turn to turn strand, coil, slot liner and ground insulation materials. It has also been used to form laminates with other materials, such as DuPont™ Nomex® paper or mica insulations, to provide a tailored electrical insulation property.

Applications


- AC Inverter Duty Motors
- Rail, Automotive Traction Motors
- Hydro, Wind Power Generators
- Transformers

Table 1 - Typical Physical Properties

Property	Unit	Typical Value	Test Method
Thickness	mil	1	ASTM D374
	µm	25.4	
Tensile Strength	kpsi	33	ASTM D882
	MPa	228	
Elongation	%	70	ASTM D882
Tensile Modulus	kpsi	545	ASTM D882
	GPa	3.8	
Dielectric Strength	V/mil	6400	ASTM D149
	kV/mm	252	
Dielectric Constant @ 1 kHz	-	3.4	ASTM D150
Dissipation Factor @ 1 kHz	-	0.002	ASTM D150
Volume Resistivity	ohm-cm	>10 ¹⁶	ASTM D257
Yield	ft ² /lb	125	-
	m ² /kg	25.5	
Density	g/cc	1.55	ASTM D1505
UL Electrical RTI	°C	240	UL 746B
UL Mechanical RTI	°C	200	UL 746B
Flammability	UL-94	V-0	UL Test Method

Voltage Endurance of Film Subject to Partial Discharge Hours to Failure - ASTM D2275 -
1/2" Diameter Electrodes, 5th out of 9

Figure 1—Comparison of Voltage Endurance, DuPont™ Kapton® 100CRC to DuPont™
Kapton® 100HN



For more information on DuPont™ Kapton® or other
DuPont products, please visit our website.

kapton.com

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5.

DuPont™, the DuPont Oval Logo, and Kapton® are trademarks or registered trademarks of DuPont or its affiliates. Copyright © 2019 DuPont de Nemours Inc. K-28402 (04/19)