



DUPONT™ TEMPRION™ OHS

ORGANIC HEAT SPREADER

DESCRIPTION

DuPont™ Temprion™ OHS is a flexible, all-polymeric heat spreader film comprising a heat-spreading core coated with a thermally conductive adhesive on one or both sides. Temprion™ OHS possesses exceptional in-plane thermal conductivity that is 250x greater than its through-plane thermal conductivity. This high ratio enables uniform heat distribution across a substrate, while maintaining thermal insulation of the substrate.

The organic nature of Temprion™ OHS provides inherent electrical insulation, eliminating the need for a coverlay to protect sensitive electronics from the electrically conductive flakes associated with traditional graphite-based heat spreaders. The flexibility of the material enables unique 3D applications.

APPLICATIONS

- Heat spreader/pipe
- Displays
- Power electronics
- Battery cell isolation
- Package wrap

FEATURES

- High in-plane thermal conductivity
- Low through-plane thermal conductivity
- Electrically insulating
- Flexible
- High mechanical integrity

Table 1 – Typical Properties of DuPont™ Temprion™ OHS Film

Property	OHS UC060000N000	Test Method
Thermal Conductivity		
In-plane (machine direction), W/m•K	45	Angstrom Method
In-plane (transverse direction), W/m•K	0.2	Angstrom Method
Through-plane, W/m•K	0.2	ASTM D5470
Young's Modulus (machine direction), GPa	140	ASTM D882
Young's Modulus (transverse direction), GPa	3	ASTM D882
Tensile Strength* (machine direction), GPa	2	ASTM D882
Elongation to Break* (machine direction), %	2.1	ASTM D882
Dielectric Strength, kV/mil	2.0	ASTM D149
Dielectric Constant, @ 1 MHz	2.2	ASTM D150
Surface Resistivity, Ω	$> 10^{15}$	ASTM D257
Volume Resistivity, $\Omega\cdot\text{cm}$	$> 10^{15}$	ASTM D257
Operating Temperature, °C	-40 to +125	N/A
RoHS Compliant	Yes	N/A

*Tensile strength and Elongation to break in the transverse direction cannot be measured due to splitting of material

www.temprion.dupont.com

Copyright © 2018 DuPont. All rights reserved. The DuPont Oval Logo and DuPont™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experiments. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-4. K-29283 (12/18)