

# DuPont QM21

SILVER/PALLADIUM CONDUCTOR

## Technical Data Sheet

### Product Description

DuPont QM21 silver/palladium Conductor is part of the DuPont QM System, a silver-based system for low cost multilayers. DuPont QM21 silver/palladium is recommended as a top conductor for component attach, as resistor terminations and large aluminum wire bond pads.

### Product Benefits

- Excellent solderability on both alumina and DuPont QM42 dielectric.
- Bondable with thick (250µm) aluminum wire
- Optimized for 30-minute firing, 850°C profiles.

### Processing

#### Substrates

Properties are based on tests on 96% alumina substrates. Substrates of other compositions and from various manufacturers may result in variations in performance properties.

#### Printing

Screen-print with a 200-mesh stainless steel screen with a 12 µm emulsion thickness.

#### Drying

Allow prints to level for 5-10 minutes at room temperature. Then dry for 10-15 minutes at 150°C.

#### Firing

Fire in a well ventilated moving conveyor furnace, in air with a 30-minute cycle, to a peak temperature of 850°C.

To retain good aged adhesion on top of DuPont QM42 dielectrics, limit number of re-firing of DuPont QM21 silver/palladium to 2 and have fired thickness of 12 µm or greater.

### Typical Fired Properties

| Test  | Properties                               |
|---|--|
| Resistivity (mΩ/sq )<br>(@ 14 µm fired thickness)   | 15 - 30                                  |
| Fired thickness (µm)<br>(200-mesh) large pad  | 14 - 20<br>12 - 15                       |
| Line resolution (200-mesh)<br>on alumina (lines/spaces)[µm]<br>on QM42 (lines/spaces)[µm]                                 | 175<br>200                               |
| Solder Acceptance <sup>2</sup><br>62Sn/36Pb/2Ag @ 220°C<br>on alumina (%)<br>on QM42 (%)                                  | ≥ 98<br>≥ 95                             |
| Solder Leach Resistance<br>62Sn/36Pb/2Ag @ 230°C<br>(No. of 10s dips)<br>on alumina (cycles)<br>on QM42 (cycles)          | 8 - 10<br>7 - 10                         |
| Adhesion <sup>3</sup><br>on alumina: Initial (N)<br>Aged 48h at 150°C[N]<br>on QM42: Initial (N)<br>Aged 48h at 150°C [N] | 20 - 30<br>20 - 30<br>20 - 30<br>15 - 27 |
| Composition Properties  |  |
| Viscosity (Pa.s)<br>Brookfield HAT, UC&SP, 10 rpm, 25°C±0.2°C   | 150-230                                  |
| Thinner   | DuPont 4553                              |
| Coverage(cm <sup>2</sup> /g)<br>(Based on fired thickness of 14 µm)   | 75 - 85                                  |

<sup>2</sup> Percentage of defect free 2 mm x 2 mm squares. Alpha 611 flux.

<sup>3</sup> See the DuPont wire peel test procedure

Table 1 shows anticipated typical physical properties for DuPont QM21 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

## Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

## Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

Copyright © 2009 DuPont. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Green Tape™ and all products or words denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates (“DuPont”).  
NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving implantation in the human body or contact with internal body fluids or tissue unless the product is provided by DuPont under a formal written contract consistent with the DuPont Policy Regarding Medical Applications of DuPont Materials H-50103-2 (“Medical Applications Policy”) and which expressly acknowledges the contemplated use. For additional information, please request a copy of DuPont Medical Caution Statement H-50102-2 and the DuPont Medical Applications Policy.

The information provided herein is offered for the product user’s consideration and examination. While the information is based on data believed to be reliable, DuPont makes no warranties, expressed or implied as to the data’s accuracy or reliability and assumes no liability arising out of its use. The data shown are the result of DuPont laboratory experiments and are intended to illustrate potential product performance within a given experimental design under specific, controlled laboratory conditions. While the data provided herein falls within anticipated normal range of product properties based on such experiments, it should not be used to establish specification limits or used alone as the basis of design. It is the product user’s responsibility to satisfy itself that the product is suitable for the user’s intended use. Because DuPont neither controls nor can anticipate the many different end-uses and end-use and processing conditions under which this information and/or the product described herein may be used, DuPont does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the products for their particular purpose.

The product user must decide what measures are necessary to safely use the product, either alone or in combination with other products, also taking into consideration the conditions of its facilities, processes, operations, and its environmental, health and safety compliance obligations under any applicable laws.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe any patent.



*The miracles of science™*

For more information on DuPont QM21 or other DuPont Microcircuit Materials products, please contact your local representative:

### Americas

DuPont Microcircuit Materials  
14 T.W. Alexander Drive  
Research Triangle Park, NC 27709  
Tel.: 800-284-3382

### Europe

Du Pont (U.K.) Limited  
Coldharbour Lane  
Bristol BS16 1QD  
U.K.  
Tel.: 44-117-931-3191

### Asia

DuPont Kabushiki Kaisha  
Sanno Park Tower, 11-1  
Nagata-cho 2-chome  
Chiyoda-ku, Tokyo 100-611  
Japan  
Tel.: 81-3-5521-8650

DuPont Taiwan Ltd  
45, Hsing-Pont Road,  
Taoyuan, Taiwan 330  
Tel.: 886-3-377-3616

DuPont China Holding Co. Ltd  
Bldg 11, 399 Keyuan Rd., Zhangji Hi-Tech Park,  
Pudong New District, Shanghai 201203, China  
Tel.: 86-21-6386-6366 ext.2202

DuPont Korea Inc.  
3~5th Floor, Asia tower #726,  
Yeoksam-dong, Gangnam-gu  
Seoul 135-719, Korea  
Tel.: 82-10-6385-5399

E. I. DuPont India Private Limited  
7th Floor, Tower C, DLF Cyber Greens,  
Sector-25A, DLF City, Phase-III,  
Gurgaon 122 002 Haryana, India  
Tel.: 91-124-4091818

Du Pont Company (Singapore) Pte Ltd  
1 HarbourFront Place, #11-01  
HarbourFront Tower One,  
Singapore 098633  
Tel.: 65-6586-3022

<http://mcm.dupont.com>