

Specialty Lubricants

MOLYKOTE® S-1501 High Temperature Synthetic Chain Oil

Synthetic oil for lubricating metal chains even at very high temperatures (+250°C/482°F)

FEATURES

- Wide service temperature range (-25°C/-13°F to +250°C/482°F)
- Longer lubrication intervals even at very high temperatures (up to 250°C/482°F)
- Low evaporation rate

COMPOSITION

- Mixture of synthetic oils
- Corrosion inhibitors
- EP additives
- Oxidation inhibitors

APPLICATIONS

- Suitable and used for oil-lubricated chains in lacquering plants and drying installations.

TYPICAL PROPERTIES

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

ASTM*	Parameter	Unit	Value
	Color		Yellowish, transparent
	Density, viscosity		
D-4052	Density at 15°C (59°F)	g/cm ³	0.980
D-445	Viscosity at 40°C (104°F)	mm ² /s	125-140
D-445	Viscosity at 100°C (212°F)	mm ² /s	10.5-12.5
	Temperature		
	Service temperature	°C	-25 to +250
		°F	-13 to +482
D-92	Flash point	°C	>250
		°F	>482
	Evaporation rate after 24 hours at 200°C (392°F)	%	<2.5
	Oxidation resistance after 4 hours at 200°C (392°F), 200ml O ₂ /minute, weight loss	%	<10
	Load-carrying capacity, wear protection, service life		
D-4172	FBM (1 hour/400N/1.200rpm) wear scar diameter	mm	<0.50
D-2783	FBM, weld load	N	1,800

* ASTM: American Society for Testing and Materials

HOW TO USE

How to apply

Apply with brush, spray-can, spray gun, drop-feed oiler or conventional metering devices. MOLYKOTE S-1501 Oil can also be applied by dipping.

HANDLING PRECAUTIONS

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning website at www.dowcorning.com. You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

USABLE LIFE AND STORAGE

When stored at or below 20°C (68°F) in the original unopened containers, this product has a usable life of 60 months from the date of production.

PACKAGING

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest Dow Corning sales office or Dow Corning distributor.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, www.dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

WE HELP YOU INVENT THE FUTURE.™

www.dowcorning.com