

Molykote[®] D-10-GBL Anti-Friction Coating

FEATURES

- Excellent resistance to oil, grease, gasoline, diesel and solvents
- Long-term wear protection
- Highly viscous and suitable for screen-printing
- High temperature resistance

COMPOSITION

- Solid lubricants
- Organic binder
- Solvent

Heat-curing dry film lubricant

APPLICATIONS

- For metal/metal combinations involving slow to medium speeds and low to medium loads.
- Suitable for the permanent lubrication of heavily loaded friction contacts involving low to high speeds, in direct contact with motor oils, gasoline, diesel or grease.
- Used in automotive applications like pistons of internal gasoline and diesel combustion engines, compressors and piston pumps, pneumatic and hydraulic systems; and other applications that require help to reduce piston and cylinder wall wear during break-in, cold-start and ongoing operation situations.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test*	Property	Unit	Result
	Color		Grey-black
	Service temperature range (cured dry film)	°C	-40 to +340
		°F	-40 to +644
	Physical properties		
ASTM-D 1084 Method B	Dynamic viscosity at 23°C (73°F)	mPas	35000
ASTM-D 1475	Density at 23°C (73°F)	g/ml	1.30
ASTM-D 56	Flash point	°C	77
		°F	171
	Load-carrying capacity, wear protection, service life		
ASTM-D 2625	Falex, procedure B, load-carrying capacity	N	p ₍₁₎ =5500
DIN 51834	SRV, Endurance life	h	s > 12
	cylinder/disc, load 50 N (150 MPa)	μ	0.12
	speed=120 mm/s, 50°C, (122°F), 40% rel.humidity, 3 drops engine oil		

*ASTM: American Society for Testing and Materials.

DIN: Deutsche Industrie Norm.

p₍₁₎=Mn-phosphated, s=sand blasted, μ = coefficient of friction

HOW TO USE

Surface preparation

First clean and degrease thoroughly the surface which will be coated with *Molykote[®] D-10-GBL Anti-Friction Coating*. Phosphating or sandblasting (180 grid) increases the adhesion and service life.

How to apply

Stir the *Molykote D-10-GBL Anti-Friction Coating* thoroughly before applying by screen printing. Recommended dry film thickness: 15 to 20μm.

It can also be applied by other processes like spraying, brushing; in this case depending on the application

process the Anti-Friction Coating should be diluted to the suitable application viscosity.

Curing

Typical curing schedule at object temperature is 20 minutes at 200°C (392°F). A flash-off of the solvent for 10 min at 80°C (176°F) prior high temperature curing is recommended. Actual curing times vary with substrate material, size, mass, coating thickness and type of curing oven; to assure proper cure and adhesion of the Anti-Friction Coating specific tests should be performed before fixing application process specifications.

Thinner

Thinning (viscosity adjustment) can be carried out by using the solvent GBL (Gamma-Butyrolactone – CAS # 96-48-0).

Coverage

When applied at 20 µm dry film thickness *Molykote* D-10-GBL Anti-Friction Coating has a coverage of approx. 15 m²/kg (this value does not take into account the losses generated during the application process).

HANDLING

PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEB SITE AT DOW CORNING.COM, OR FROM YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.

USABLE LIFE AND STORAGE

When stored at or below 23°C (73°F) in the original unopened containers *Molykote* D-10-GBL Anti-Friction Coating has a usable life of 12 months from the date of production. Storage containers in cool and dark place (avoid direct sun light exposure).

PACKAGING INFORMATION

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest Dow Corning sales office or Dow Corning distributor.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our Web site, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

We help you invent the future.™

molykote.com