

Specialty Lubricants

MOLYKOTE® 7514 Synthetic Grease

FEATURES

- Wide service temperature range
-40 to +180°C (-40 to 356°F)
- Suitable for long term lubrication
- Good low temperature performance
- Good protection against corrosion

COMPOSITION

- PAO/Ester base oil
- Lithium complex thickener
- EP additives
- Corrosion inhibitors

Synthetic (PAO/Ester) grease especially for intermediate transmissions of starter motors

APPLICATION

- Used successfully for needle bearings in planetary gears.

TYPICAL PROPERTIES

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

Standard*	Test	Unit	Value
	Color		Light brown
	Consistency, density, viscosity		
DIN 51 818	NLGI consistency class		1-2
ISO 2137	Worked penetration	mm/10	290-320
ISO 2811	Density at 20°C (68°F)	g/ml	0.9
DIN 51 562	Base oil viscosity at 40°C (104°F)	mm ² /s	49
	Temperature		
	Service temperature	°C	-40 to +180
		°F	-40 to +356
ISO 2176	Dropping point	°C	>200
		°F	>392
DIN 51 805	Kesternich method - flow pressure at -40°C (-40°F)	mbar	<800
	Resistance		
DIN 51 808	Oxidation resistance, pressure drop after 100h, 99°C (210°F)	bar	0.1
	Corrosion protection		
DIN 51 802	SKF-Emcor method - degree of corrosion		0

* DIN: Deutsche Industrie Norm.

ISO: International Standardisation Organisation.

HOW TO USE

Clean points of contact. Apply in the same way as lubricating greases, using brush, spatula or automatic lubrication device. Can be used in central lubrication systems.

HANDLING PRECAUTIONS

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning website at www.dowcorning.com. You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

USABLE LIFE AND STORAGE

When stored at or below 20°C (68°F) in the original unopened containers, this product has a usable life of 60 months from the date of production.

PACKAGING

This product is available in various container sizes. Detailed information on container size should be obtained from your nearest Dow Corning sales office or Dow Corning distributor.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, www.dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

WE HELP YOU INVENT THE FUTURE.™

www.dowcorning.com