



WATER TREATMENT AT POWER PLANT

Pressurized Water Reactor Chemical & Volume Control System (Primary Loop Chemistry)

Resins used for nuclear power primary side chemical control must purify water in a lithium or potassium and borate environment. Our IRN-grade ion exchange resins have proven to be the premier resins chosen to protect nuclear power plants throughout the world.

PRODUCT	APPLICATION	FEATURES AND RECOMMENDED USES	TYPE	MATRIX	MINIMUM TOTAL VOLUME CAPACITY (eq/L)
AMBERLITE™ IRN77 H	Delithiation	All purpose cation resin for multiple nuclear applications. 8% DVB uniform particle size cation resin with high capacity. Used for control of 7Li or K content of in the reactor coolant and removal of cationic impurities.	SAC	GEL	1.90
AMBERLITE™ IRN97 H	Delithiation/ CANDU Moderator	High capacity 10% DVB uniform particle size cation resin for primary side purification and control of 7Li or K content of the reactor coolant.	SAC	GEL	2.10
AMBERLITE™ IRN99 H	Delithiation/ CANDU Moderator	Premium 16% DVB uniform particle size cation resin with very high capacity and oxidative stability. Highest Cs selectivity and capacity for long runs and reduced waste and exposure. The high oxidative stability results in reduced reactor water sulfate concentration in PWR primary applications.	SAC	GEL	2.50
AMBERLITE™ IRN360 H/OH	Delithiation & CVCS	Gel type mixed bed composed of 2/3 high capacity UPS cation resin AMBERLITE™ IRN97 H and 1/3 AMBERLITE™ IRN78 OH Resins on a volume basis. High cation content allows its use for Lithium control like a cation resin, then as a CVCS mixed bed when exhausted in Lithium.	MB	GEL/GEL	2.10/1.20
AMBERLITE™ IRN9652 H	CVCS	20% DVB macroporous cation resin with large pore structure for colloid removal. Used as cation overlay. Very high selectivity for 137Cs.	SAC	MACRO	1.95
AMBERLITE™ IRN9675 H	CVCS	Nuclear grade macroporous cation resin designed to remove radioactive colloidal material in all nuclear applications. Often used as an overlay above a mixed bed.	SAC	MACRO	1.70
AMBERLITE™ IRN78 OH	Deboration	Premium high solids uniform particle size anion resin with very high capacity. Used for removal of anionic radioisotopes and deboration with a high capacity for boron. Specifically processed to minimize organic chloride content.	SBA	GEL	1.20
AMBERLITE™ IRN9766 OH	CVCS	Macroporous anion resin designed to remove radioactive colloidal material in all nuclear applications. Often used as an overlay above a mixed bed or a cation resin.	SBA	MACRO	0.85
AMBERLITE™ IRN150 H/OH	CVCS	Nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN77 H and IRN78 OH Resin on a 1:1 equivalent basis.	MB	GEL/GEL	1.90/1.20
AMBERLITE™ IRN160 H/OH	CVCS / CANDU Moderator / Pre-outage clean-up	High capacity nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN97H and IRN78 Resins on a 1:1 equivalent basis. Designed to minimize separation of anion and cation during installation and transfer.	MB	GEL/GEL	2.10/1.20
AMBERLITE™ IRN170 H/OH	CVCS / CANDU Moderator / Pre-outage clean-up	Premium nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN99 and IRN78 Resins on a 1:1 equivalent basis. Offers maximum oxidative stability and highest operating capacity to achieve the lowest reactor water sulfate concentration and longest resin life.	MB	GEL/GEL	2.50/1.20
AMBERLITE™ IRN9882 H/OH	Pre-outage clean-up	Nuclear grade macroporous mixed bed composed of 40% cation resin (12%DVB) and 60% AMBERLITE™ IRN9766 OH Resin on a volume basis. Offers high exchange kinetics and the ability to remove colloids to achieve the fastest decontamination pre outage.	MB	MACRO/MACRO	1.65/0.85
AMBERLITE™ IRN164 Li/OH	CANDU Heat Transport System	Nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN97 H Resin loaded with natural Li and AMBERLITE™ IRN78 OH on a 1:1 equivalent basis for CANDU heat transport system purification.	MB	GEL/GEL	2.20/1.20
AMBERLITE™ IRN217 Li/OH	CVCS	Nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN77 H Resin loaded with 7Li at ≥ 99.9% of isotopic purity and AMBERLITE™ IRN78 OH on a 1:1 equivalent basis for primary side purification with robust pH control.	MB	GEL/GEL	1.90/1.20
AMBERLITE™ IRN317 Li/OH	CVCS	Premium nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN99 H Resin loaded with 7Li at ≥ 99.9% of isotopic purity and AMBERLITE™ IRN78 OH on a 1:1 equivalent basis offering the highest operating capacity for long resin life, less waste and reduced exposure.	MB	GEL/GEL	2.50/1.20

Key:

SBA = Strong Base Anion
SAC = Strong Acid Cation
MB = Mixed Bed

Powering performance worldwide.

With a large global manufacturing footprint, strong R&D expertise and technical support services and systems, we supply high market volumes with high quality. Dow partners with you, our customer, to understand unmet needs and develop tailored solutions.

● RESEARCH & DEVELOPMENT

Chauny, France*
Collegetown, PA*
Edina, MN*
Huzhou, China
Kaust Jeddah, KSA
Midland, MI*
Shanghai, China*
Tarragona, Spain**

*DW&PS Technology Center
**Global Water Technology Center

● COMMERCIAL OPERATIONS

Astana, Kazakhstan
Bangkok, Thailand
Budapest, Hungary
Dubai, UAE
Horgen, Switzerland
Johannesburg, South Africa
Kuala Lumpur, Malaysia
Moscow, Russia
Mumbai, India
Nairobi, Kenya
Rheinmünster, Germany
São Paulo, Brazil
Seoul, Korea
Sydney, Australia
Tokyo, Japan
Warsaw, Poland

● MANUFACTURING

Chauny, France
Edina, MN
Fombio, Italy
Huzhou, China
Jubail Industry City, Saudi Arabia
Menlo Park, CA
Midland, MI
Qingpu, China
Soma, Japan



Water & Process Solutions

7600 Metro Blvd.
Edina, MN 55439

For more information, contact our Customer Information Group:

Asia Pacific	+86 21 3851 4988
Europe, Middle East, Africa	+31 115 672626
Latin America	+55 11 5184 8722
North America	1-800-447-4369

dowwaterandprocess.com

WARNING: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN EXCEPT FOR ANY SPECIFIC WARRANTY SET FORTH HEREIN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. Nothing in this document should be treated as a warranty by Dow.

Printed in the U.S.A.

©™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

Form No. 177-03676-0518 CDP