

WATER TREATMENT AT POWER PLANT

Steam Generator Blowdown

Product Recommendations

A steam generator blowdown (SGBD) system purifies the water in steam generators to minimize corrosion and reduce ionic hideout. A low percentage of the total flow is directly removed from the steam generators and treated by ion exchange. The run length of the resin bed is determined by sodium leakage or other impurities; therefore, ion exchange resins must have high capacity and high selectivity for the impurities to be removed.

PRODUCT	FEATURES AND RECOMMENDED USES	ТҮРЕ	MATRIX	MINIMUM TOTAL VOLUME CAPACITY (eq/L)	IONIC FORM AS SHIPPED
AMBERLITE™ IRN99 H	Premium 16% DVB uniform particle size cation resin with very high Na selectivity, total capacity, and oxidative stability. Provides long resin life when operating in the amine form. Ready to use resin for non-regenerable units. Highly controlled for low sodium traces.	SAC	GEL	2.50	H+
AMBERLITE™ IRN97 H	High capacity 10% DVB uniform particle size cation resin for plants operating in the H/OH cycle or in the ammonia cycle. Ready to use resin for non-regenerable units. Highly controlled for low sodium traces.	SAC	GEL	2.10	H+
AMBERLITE™ IRN77 H	Uniform particle size gel cation resin processed to the highest purity standards required for treating water in the nuclear power industry.	SAC	GEL	1.90	H ⁺
AMBERLITE™ IRN9652 H	High capacity 20% DVB macroporous cation resin. Highest selectivity for Na in organic amine form operation providing the longest resin life, mainly in morpholine conditioning. Ready to use resin for non-regenerable units.	SAC	MACRO	1.95	H+
AMBERLITE™ IRN78 OH	Premium high solids uniform particle size anion resin with very high capacity. Specifically processed to minimize organic chloride content. Ready to use resin for non-regenerable units.	SBA	GEL	1.20	OH-
AMBERLITE™ HPR2000 H	20% DVB uniform particle size macroporous cation resin with very high Na selectivity and oxidative stability. Providing long resin life when operating in the amine form. Best used in regenerable mixed beds.	SAC	MACRO	1.70	H+
AMBERLITE™ HPR1600 H	Premium 16% DVB uniform particle size cation resin with very high Na selectivity, total capacity, and oxidative stability. The larger particle size of AMBERLITE™ HPR1600 H makes it the right choice when pressure drop is a concern. Best used in regenerable mixed beds.	SAC	GEL	2.40	H+
AMBERLITE™ HPR9000 OH	Macroporous anion resin providing excellent resistance to surface fouling. Best used in regenerable mixed beds.	SBA	MACRO	0.80	OH-
AMBERLITE™ IRN150 H/OH	Nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN77 H and IRN78 OH on a 1:1 equivalent basis for full demineralization.	МВ	GEL/GEL	1.90/1.20	H+/OH-
AMBERLITE™ IRN160 H/OH	High capacity nuclear grade mixed bed composed of uniform particle size AMBERLITE™ IRN97 H and IRN78 OH on a 1:1 equivalent basis. Designed to minimize separation of anion and cation during installation and transfer.	MB	GEL/GEL	2.10/1.20	H+/OH-
AMBERLITE™ HPR650 H	Ready to use, high capacity uniform gel type resins combination for normal operation in circuit #5 of VVER. This combination of high	SAC	GEL	2.00	H ⁺
AMBERLITE™ HPR550 OH	exchange capacity strong acid cation and strong base anion is the ideal combination for achieving high operating capacity. Best used in regenerable mixed beds.	SBA	GEL	1.10	OH-

Key:

SBA = Strong Base Anion SAC = Strong Acid Cation

Powering performance worldwide.

With a large global manufacturing footprint, strong R&D expertise and technical support services and systems, we supply high market volumes with high quality. Dow partners with you, our customer, to understand unmet needs and develop tailored solutions.

RESEARCH & DEVELOPMENT

Chauny, France*
Collegeville, PA*
Edina, MN*
Huzhou, China
Kaust Jeddah, KSA
Midland, MI*
Shanghai, China*
Tarragona, Spain**

*DW&PS Technology Center **Global Water Technology Center

COMMERCIAL OPERATIONS

Seoul, Korea Sydney, Australia Tokyo, Japan Warsaw, Poland

Astana, Kazakhstan Bangkok, Thailand Budapest, Hungary Dubai, UAE Horgen, Switzerland Johannesburg, South Africa Kuala Lampur, Malaysia Moscow, Russia Mumbai, India Nairobi, Kenya Rheinmünster, Germany São Paulo, Brazil

MANUFACTURING

Chauny, France Edina, MN Fombio, Italy Huzhou, China Jubail Industry City, Saudi Arabia Menlo Park, CA Midland, MI Qingpu, China Soma, Japan



Water & Process Solutions

7600 Metro Blvd. Edina, MN 55439

For more information, contact our Customer Information Group:

Asia Pacific +86 21 3851 4988
Europe, Middle East, Africa +31 115 672626
Latin America +55 11 5184 8722
North America 1-800-447-4369

dowwaterandprocess.com

WARNING: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN EXCEPT FOR ANY SPECIFIC WARRANTY SET FORTH HEREIN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. Nothing in this document should be treated as a warranty by Dow.

Printed in the U.S.A.