




AMBERLITE™ SCAV4 Cl Ion Exchange Resin

Gaussian, Macroporous, Acrylic, Organic Scavenging Resin for Industrial Applications

Description

AMBERLITE™ SCAV4 Cl Ion Exchange Resin is a scavenger to effectively remove natural organic matter (NOM) from waters under different operational circumstances, bringing water quality and operational stability back under control.



The macroporous structure allows very efficient removal of large organic molecules and provides excellent resistance to physical breakdown by attrition and osmotic shock. The hydrophilic acrylic polymer structure contributes to a more effective desorption of organics during regeneration compared to styrenic scavenger resins.

AMBERLITE SCAV4 Cl is the preferred organic scavenger for the bulk removal of NOM. Operated in the Cl-form, it is especially useful as pretreatment for reverse osmosis or demineralization systems to reduce the fouling potential of water with a high load of hydrophilic and/or hydrophobic NOM species. The resin offers excellent lifetime and long, stable performance, even under challenging operational conditions.

Operated in the OH-form, this resin will also have the ability to demineralize.

Applications

- Organic scavenging
- Reverse osmosis pretreatment
- Demineralization

System Designs

- Co-current

Historical Reference

AMBERLITE™ SCAV4 Cl Ion Exchange Resin has previously been sold as AMBERLITE™ IRA958 Cl Ion Exchange Resin.

Typical Physical and Chemical Properties**

Physical Properties	
Copolymer	Crosslinked acrylic
Matrix	Macroporous
Type	Strong base anion, Type I
Physical Form	White, opaque, spherical beads
Chemical Properties	
Ionic Form as Shipped	Cl ⁻
Total Exchange Capacity	≥ 0.80 eq/L (Cl ⁻ form)
Water Retention Capacity	66.0 – 72.0% (Cl ⁻ form)
Particle Size	
Particle Diameter §	630 – 850 μm
< 300 μm	≤ 0.5%
> 1180 μm	≤ 5.0%
Stability	
Whole Uncracked Beads	≥ 95%
Density	
Particle Density	1.06 g/mL
Shipping Weight	700 g/L

§ For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 177-01775).

Suggested Operating Conditions**

Temperature Range	
OH ⁻ form	5 – 35°C (41 – 95°F)
Cl ⁻ form	5 – 80°C (41 – 176°F)
pH Range	
Service Cycle	2 – 10
Stable	0 – 14

For additional information regarding recommended minimum bed depth, operating conditions, and regeneration conditions for [scavenger resins](#) (Form No. 177-03929) in water treatment, please refer to our Tech Fact.

Hydraulic Characteristics

Estimated bed expansion of AMBERLITE™ SCAV4 Cl Ion Exchange Resin as a function of backwash flowrate and temperature is shown in Figure 1.

Estimated pressure drop for AMBERLITE SCAV4 Cl as a function of service flowrate and temperature is shown in Figure 2. These pressure drop expectations are valid at the start of the service run with clean water and a well-classified bed.

Figure 1: Backwash Expansion

Temperature = 10 – 60°C (50 – 140°F)





Figure 2: Pressure Drop

Temperature = 10 – 60°C (50 – 140°F)



Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

For more information, contact our Customer Information Group:

Asia Pacific	+86 21 3851 4988
Europe, Middle East, Africa	+31 115 672626
Latin America	+55 11 5184 8722
North America	1-800-447-4369

www.dowwaterandprocess.com

WARNING: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

**All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. Nothing in this document should be treated as a warranty by Dow.

