

DuPont™ Cyrel® VSA

Solvent Process Analogue Plate for Varnishing

Applications

- Aqueous coating
- UV-Lacquer
- Metallic ink



The DuPont™ Cyrel® VSA plates are ideal for varnishing and special effect ink and coatings applications. Cyrel® VSA plates offer high quality print finishing on folding cartons, such as food packaging, cigarettes, cosmetics, etc. They are also used in commercial printing for spot coating of catalogues, calendars, books and brochures.

Product Features

- Excellent coating and ink transfer permits superior coating
- High resolution and exact register results in fine detail and complex forms can be spot coated and printed in the coating tower
- High durability for long print runs
- Image relief is clean and sharp
- Can be used again and again without any loss of registration

Printing Ink and Solvent Compatibility

Cyrel® VSA plates offer excellent compatibility with UV-lacquers and water-based inks. The enforced polyester base will maintain accurate registration even with large plates.

Process of Use

Expose the plate through the back to establish the floor and maximize sensitivity. Back exposure varies according to relief required. Remove the protective coversheet and expose the front of the plate. Process the plate in the Cyrel® plate processor. Finish the plate in a light finisher to eliminate surface tackiness. Post-expose the plate to ensure complete polymerisation.

Storage-Raw Material

Store unexposed plates in a cool area (4–32°C, 40–90°F), away from direct sources of heat. Humidity control is not required. Cyrel® VSA is foam interleaved to provide maximum protection of the plate after manufacture and during transportation and storage. Plates should be stacked flat. Plates should not be exposed to direct sunlight or excessive white light. Continuous exposure to very high ozone concentrations should be avoided.

Handling – Raw Material

Like all photopolymer plates, Cyrel® VSA plates should be handled under UV free light; e.g. fluorescent tubes covered with amber sleeves.

Storage – Finished Plates

After printing, plates should be thoroughly cleaned with a compatible solvent before storing. They may be stored on cylinders, sleeves or demounted and stored flat.

DuPont™ Cyrel® VSA

Solvent Process Analogue Plate for Varnishing

Technical Data

	Thickness	Durometer	Image Reproduction	Min. Positive Line Width	Min. Isolated Dot Size	Relief Depth	Processing
Cyrel® VSA	1,14 mm/0,045"	73 Sh A	2–95% / 48 L/cm	0,25 mm	250 µm	0,4–0,5 mm / 0,016–0,020"	Solvent / Analogue

DuPont Advanced Printing brings together leading technologies and products for the printing and package printing industries. DuPont™ Cyrel® is one of the world's leading flexographic platemaking systems in digital and conventional formats, including DuPont™ Cyrel® brand photopolymer plates (analogue and digital), Cyrel® platemaking equipment, Cyrel® round sleeves, Cyrel® plate mounting systems and the revolutionary Cyrel® FAST thermal system.



cyrel.eu

For more information on DuPont™ Cyrel® or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

DuPont™, the DuPont Oval Logo, and Cyrel® are trademarks or registered trademarks of DuPont or its affiliates. Copyright © 2020 DuPont de Nemours Inc. All rights reserved.

PDS-EU0041-EN (11/20)