

ENERGY
Oil & Gas



DuPont™ Kalrez® Spectrum™ 7375 Perfluoroelastomer Parts


High Temperature Broad Chemical & Water/Steam Resistance



Excellent broad chemical resistance & seal force retention in hot water/steam

DuPont™ Kalrez® 7375 perfluoroelastomer parts are designed to reliably seal in the most demanding chemical and hot water/steam environments. Thermally stable up to 300 °C, Kalrez® 7375 parts can meet your 80 durometer (Shore A) perfluoroelastomer (FFKM) specifications in numerous shapes and configurations.

Compression Stress Relaxation (CSR) in water* at 225 °C measured at 90 °C



*O-rings tested by compression stress relaxation per SAE J2979 at 20% compression per SAE J2979

Typical Applications


- Completion tools
- Drilling and wireline tools
- Valves
- Pumps
- Compressors
- Process instrumentation
- Packing systems

Compatible with amines¹ commonly used in the O&G industry

Volume change² (%) after 672 hours in several amines at 90 °C

¹Examples below represent typical analogs of amines found in drilling fluids, corrosion inhibitors, pump oil additives, etc.

²Volume change (%) is a good predictor of performance and low values typically translate to compatibility in the chemical environment. Test performed with AS-568 K214 O-rings.



Suitable for use in sour service

Tested using the rigorous requirements of ISO 23936-2 at 215 °C after long term exposure to high H₂S content mixture.


- Hardness within +5/-20 points
- Volume change within +25% / -5%
- M50, Tb, and Eb retention within +/- 50%


Electrical properties

Kalrez® 7375 parts exhibit excellent insulative properties making it an ideal perfluoroelastomer for use in harsh oil & gas applications such as electrical connectors/boots.

Custom sealing solutions

Our global technology network enables us to collaborate with you to provide a customized design solution to meet your unique sealing needs.





Visit us at kalrez.com

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2021 DuPont. All rights reserved.



dupont.com

(10/2021) Reference: KZE-A40106-00-A1021