



# DUPONT™ INTEXAR™ PE874

## STRETCHABLE SILVER CONDUCTOR

### PRODUCT DESCRIPTION

DuPont™ Intexar™ PE874 is a high recovery stretchable silver conductor paste for printed low-voltage circuitry on elastomeric film and textile substrates. PE874 is a silver-bearing conductor that possesses excellent stretchability, adhesion, and conduction. It is compatible with polyurethane (TPU) film and select synthetic fabrics.

### PRODUCT BENEFITS

- High recovery stretchable conductor
- Washable with proper encapsulation
- Compatible with wide variety of fabric and film substrates
- Compatible with lamination

### PROCESSING

#### Screen Printing Equipment

- Automatic reel-to-reel
- Semi-automatic flat-bed
- Rotary screen/cylinder screen

#### Substrates

- Select synthetic fabrics
- Coated fabrics & membranes
- Thermoplastic polyurethane films

#### Screens

- 325 – 200 Wire/inch stainless steel mesh
- 120 – 77 Thread/cm polyester mesh

#### Curing

Dry at 130°C for 15 minutes in a well-ventilated oven or conveyor dryer, where the exhaust meets environmental regulations. Drying efficiency and good print quality/thickness control helps ensure best electrical and physical performance.

Table 1-Typical Physical Properties

Test	Properties
Resistivity (mΩsq/25μm) (5μm Dried Print Thickness on ST505 PET Film)	<50
Resistivity After Crease (ASTM F1683, 180deg, 1 cycle, 2kg)	<5%
Abrasion Resistance (ASTM D3363 Pencil Hardness)	1H
Adhesion (Tape Cross Hatch) (ASTM D3359 w/3M Scotch Tape 600)	No Transfer
Clean-Up Solvent	Ethylene Diacetate
Encapsulant	PE773
Color	Metallic

Table 2-Typical Composition Properties

Test	Properties
Solids (%) @ 150°C	63 – 68
Viscosity (PaS) Brookfield RVT, #14 spindle, 10rpm, 25°C	20 – 60
Density (g/cc)	2.41
Dried Print Thickness (microns)	8 – 12
Thinner	DuPont™ 8260

Printed on Melinex ST505 Polyester Film. This table shows anticipated typical physical properties for DuPont™ Intexar™ PE874 based on specific experiments and is not intended to represent the product specifications. Product specifications are available upon request.

### SUBSTRATE TYPES

PE874 is appropriate for many types of thermally-stable substrates in wearable electronics applications. Due to the diverse nature of potential fabrics and films that could be considered, it is not always possible to provide detailed performance guidance. For more information, please call your local DuPont representative.



## DUPONT™ INTEXAR™ PE874 STRETCHABLE SILVER CONDUCTOR

### STORAGE AND SHELF LIFE

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use. Thinning with DuPont™ 8260 may be desired in some cases depending on printing requirements.

### SAFETY AND HANDLING

Please inform the DuPont product supplier if you intend to test PE874, alone or in combination with other materials, on human skin. For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

### FOR MORE INFORMATION ON DUPONT™ INTEXAR™ PE874 OR OTHER DUPONT MICROCIRCUIT MATERIALS PRODUCTS, PLEASE CONTACT YOUR LOCAL REPRESENTATIVE:

#### Americas

DuPont Photovoltaic and Advanced Materials  
974 Centre Rd.  
Chestnut Run Plaza 708  
Wilmington DE 19805

#### Europe, Middle East & Africa

Du Pont (UK) Ltd  
Coldharbour Lane  
Bristol BS16 1QD  
UK  
Tel +44 117 931 3191

#### Asia

Du Pont Kubushiki Kaisha  
MCM Technical Lab  
DuPont Electronics Center  
KSP R&D B213, 2-1,  
Sakado 3-chome, Takatsu-ku,  
Kawasaki-shi, Kanagawa, 213-0012  
Japan  
Tel +81 44 820 7575

DuPont Taiwan Ltd  
45, Hsing-Pont Road  
Taoyuan, 330  
Taiwan  
Tel +886 3 377 3616

DuPont China Holding Company Ltd  
Bldg. 11, 399 Keyuan Road  
Zhangjiang Hi-Tech Park  
Pudong New District  
Shanghai 201203  
Tel +86 21 3862 2888

DuPont Korea Inc.  
3-5th Floor, Asia tower #726  
Yeoksam-dong, Gangnam-gu  
Seoul 135-719, Korea  
Tel +82 2 2222 5275

E.I. DuPont India Private Limited  
7th Floor, Tower C, DLF Cyber Greens  
Sector-25A, DLF City, Phase-III  
Gurgaon 122 002 Haryana, India  
Tel +91 124 409 1818

Du Pont Company (Singapore) Pte Ltd  
21 Biopolis Road,  
#06-21, Nucleos, South Tower,  
Singapore 138567  
Tel +65 6586 3022

[advancedmaterials.dupont.com](http://advancedmaterials.dupont.com)

Copyright © 2018 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and all DuPont products denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experimentations. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5.

K-29701 (6/18)