



DUPONT™ BQ10

UV CURABLE DIELECTRIC

PRODUCT DESCRIPTION

DuPont™ BQ10 is a UV curable, solventless, screen printable composition used in encapsulant and crossover applications for Bio Sensor applications. It offers the advantages of rapid cure and excellent processing latitude while maintaining excellent electrical and physical properties after cure, including excellent crosshatch adhesion to polyester and polycarbonate substrates and conductors. It is fully compatible with the DuPont Bio sensor conductor compositions.

PRODUCT BENEFITS

- Fast UV cure
- Zero VOC when properly cured
- Adhesion to polyester and polycarbonate substrates

PROCESSING

Screen Printing Equipment

Semiautomatic and manual

Substrates

Polyester; polycarbonate

Ink Residence Time on Screen

> 2 hours

Screen Types

Polyester, stainless steel

Optimum Cure Conditions for Flexibility

40 ft/min in air¹
500 - 1500 mJ/cm*

Typical Thickness

(After cure per print)

Printed with 200 mesh stainless steel screen 0.5-0.6 mils

*Two prints of dielectric are strongly recommended to achieve maximum circuit reliability.

Table 1-Typical Physical Properties and Electrical Properties on ITO Polyester Film

Test	Properties
Adhesion Crosshatch (ASTM D3359-78) Dielectric to ITO-coated Polyester/Scotch Tape#600	No transfer (5B)
Conductor to Dielectric	No transfer
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	≥ 1
Operating Use Temperature (°C)	</= 105°C
Dielectric Constant (ASTM D150)[@ 1KHz]	4.4
Insulation Resistance [GΩ/sq/mil]	> 10

Table 2-Composition Properties

Test	Properties
Viscosity (Pa.s) [Brookfield RVT, 10 rpm, #14 spindle, 25°C]	30-70
Solids (150°C)[%]	100
Coverage (cm ² /g) (Dependent on print thickness): 0.45 mil coating given by 280-mesh polyester 0.6 mil coating given by 230-mesh polyester 1.0 mil coating given by 280-mesh stainless steel 1.1 mil coating given by 200-mesh stainless steel	500 375 290 240
Thinner	Not recommended
Density, g/cm ³	1.28
Color	Green
Odor	Slight, pleasant

Table 1 & 2 show anticipated typical physical properties for DuPont™ BQ10 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.



DUPONT™ BQ10 UV CURABLE DIELECTRIC

STORAGE AND SHELF LIFE

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

SAFETY AND HANDLING

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

FOR MORE INFORMATION ON DUPONT™ BQ10 OR OTHER DUPONT MICROCIRCUIT MATERIALS, PLEASE CONTACT YOUR LOCAL REPRESENTATIVE:

Americas

DuPont Microcircuit Materials
14 TW Alexander Drive
Research Triangle Park, NC 27709
USA
Tel +1 800 284 3382 (calls within USA)
Tel +1 919 248 5188 (calls outside USA)

Europe, Middle East & Africa

Du Pont (UK) Ltd
Coldharbour Lane
Bristol BS16 1QD
UK
Tel +44 117 931 3191

Asia

Du Pont Kubushiki Kaisha
MCM Technical Lab
DuPont Electronics Center
KSP R&D B213, 2-1,
Sakado 3-chome, Takatsu-ku,
Kawasaki-shi, Kanagawa, 213-0012
Japan
Tel +81 44 820 7575

DuPont Taiwan Ltd
45, Hsing-Pont Road
Taoyuan, 330
Taiwan
Tel +886 3 377 3616

DuPont China Holding Company Ltd
Bldg. 11, 399 Keyuan Road
Zhangjiang Hi-Tech Park
Pudong New District
Shanghai 201203
Tel +86 21 3862 2888

DuPont Korea Inc.
3-5th Floor, Asia tower #726
Yeoksam-dong, Gangnam-gu
Seoul 135-719, Korea
Tel +82 2 2222 5275

E.I. DuPont India Private Limited
7th Floor, Tower C, DLF Cyber Greens
Sector-25A, DLF City, Phase-III
Gurgaon 122 002 Haryana, India
Tel +91 124 409 1818

Du Pont Company (Singapore) Pte Ltd
1 HarbourFront Place, #11-01
HarbourFront Tower One
Singapore 098633
Tel +65 6586 3022

mcm.dupont.com

Copyright © 2015 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and all DuPont products denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experiments. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 K-28877 (5/15)