

# DuPont™ Kapton® FN

## Polyimide Film

### Product Description

DuPont™ Kapton® FN is a general purpose HN film that is coated or laminated on one or both sides with FEP fluoropolymer. Kapton® FN imparts heat sealability, provides a moisture barrier, and enhances chemical resistance.

Kapton® FN is recommended in applications that require a heat bondable film, or moisture and chemical resistance beyond the capabilities of uncoated Kapton® films. A list of available constructions can be found in the DuPont™ Kapton® polyimide film general specification, EI-10167.

### Applications

- Tubing
- Heater circuits
- Heat sealable bags
- Automotive diaphragms and manifolds
- Electrical insulation

### Product Specifications

Kapton® FN is manufactured, slit and packaged according to the product specifications listed in EI-10167, DuPont™ Kapton® polyimide film general specification.

### Certification

Kapton® FN meets ASTM D5213 (type 2, item A) requirements.

**Table 1. Physical Properties of Kapton® FN Film**

Property	Typical Value for Film Type			Test Method
	120FN616	150FN019	250FN029	
Ultimate Tensile Strength, MPa (psi) at 23°C (73°F) at 200°C (392°F)	207 (30,000) 121 (17,500)	162 (23,500) 89 (13,000)	200 (29,000) 115 (17,000)	ASTM D882, Method A*
Yield Point at 3%, MPa (psi) at 23°C (73°F) at 200°C (392°F)	61 (9000) 42 (6000)	49 (7000) 43 (6000)	58 (8500) 36 (5000)	ASTM D882
Stress at 5% Elongation, MPa (psi) at 23°C (73°F) at 200°C (392°F)	79 (11,500) 53 (8000)	65 (9500) 41 (6000)	76 (11,000) 48 (7000)	ASTM D882
Ultimate Elongation, % at 23°C (73°F) at 200°C (392°F)	75 80	70 75	85 110	ASTM D882
Tensile Modulus, GPa (psi) at 23°C (73°F) at 200°C (392°F)	2.48 (360,000) 1.62 (235,000)	2.28 (330,000) 1.14 (165,000)	2.62 (380,000) 1.38 (200,000)	ASTM D882
Impact Strength at 23°C (73°F), N·cm (ft·lb)	78 (0.58)	68.6 (0.51)	156.8 (1.16)	DuPont Pneumatic Impact Test
Tear Strength, initial Graves, N (lbf)	1.8 (2.6)	1.5 (2.6)	17.8 (4.0)	ASTM D1004
Tear Strength, propagating Elmendorf, N	7.2	16.3	26.3	ASTM D1922
Density, g/cc or g/mL	1.53	1.67	1.57	ASTM D1505

\*Specimen size 25 x 150 mm (1.6 in); jaw separation 100 mm (4 in), jaw speed, 50mm/min (2 in/min). Ultimate refers to the tensile strength and elongation measured at break.

# DuPont™ Kapton® FN

Polyimide Film

**Table 2. Typical Electrical Properties of Kapton® FN Film at 23°C (73°F), 50% RH**

Property	Typical Value for Film Type			Test Method
	120FN616	150FN019	250FN029	
Dielectric Strength, V/μm (V/mil)	272 (6900)	197 (5000)	197 (5000)	ASTM D149
Dielectric Constant	3.1	2.7	3.0	ASTM D150
Dissipation Factor	0.0015	0.0013	0.0013	ASTM D150
Volume Resistivity, Ω · cm				ASTM D257
23°C (73°F)	1.4 × 10 <sup>17</sup>	2.3 × 10 <sup>17</sup>	1.9 × 10 <sup>17</sup>	
200°C (392°F)	4.4 × 10 <sup>14</sup>	3.6 × 10 <sup>14</sup>	3.7 × 10 <sup>14</sup>	

**Table 3. Chemical Properties of Kapton® FN Film**

Property	Typical Value for Film Type			Test Method
	120FN616	150FN019	400FN022	
Moisture Absorption, % at 23°C (73°F), 50% RH	1.3	0.8	0.4	ASTM D570
98% RH	2.5	1.7	1.2	
Water Vapor Permeability, g/(m <sup>2</sup> ·24 h)	17.5	9.6	2.4	ASTM E96
g/(100 in <sup>2</sup> ·24 h)	1.13	0.62	0.16	



For more information on DuPont™ Kapton® polyimide films or other DuPont products, please visit our website.

[kapton.com](http://kapton.com)

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Applications CAUTION" and "DuPont Medical Applications POLICY" statements. These documents are available upon request.

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2020 DuPont de Nemours Inc. All rights reserved.

EI-10160 (7/20)