

# Specification properties of Legacy Tyvek® 1073B and 1059B

Property	Comparable standard test method	Units	Nominal value (range)	
			Legacy Tyvek® 1073B	Legacy Tyvek® 1059B
<b>Product specifications (English units)</b>				
Basis weight	ASTM D3776 <sup>1</sup> EN ISO 536 <sup>1</sup>	oz/yd <sup>2</sup>	2.20 [2.10–2.30]	1.90 [1.82–1.98]
Delamination	ASTM D2724 <sup>2</sup>	lb <sub>f</sub>	0.5 [0.4–0.7]	0.5 [0.3–0.7]
Gurley Hill porosity	TAPPI T460 <sup>1</sup> ISO 5636-5 <sup>3</sup>	sec/100 cc	22 [8–36]	20 [8–36]
<b>Product specifications (metric units)</b>				
Basis weight	ASTM D3776 <sup>1</sup> EN ISO 536 <sup>1</sup>	g/m <sup>2</sup>	74.6 [71.2–78.0]	64.4 [61.7–67.1]
Delamination	ASTM D2724 <sup>2</sup>	N	2.3 [1.6–3.1]	2.2 [1.5–2.9]
Gurley Hill porosity	TAPPI T460 <sup>1</sup> ISO 5636-5 <sup>3</sup>	sec/100 cc	22 [8–36]	20 [8–36]

**Notes:** Specification properties are controlled to a nominal value and released within specifications. The customer is responsible for determining that Legacy Tyvek® is suitable for the intended application. The ranges represent the controlled minimum and maximum values in which the product is released. Specification properties are based on roll averages, with samples taken uniformly across the sheet. These properties are representative for uncoated Legacy Tyvek® as sold by DuPont. Any downstream operations, such as coatings applied by sterile packaging manufacturers (SPMs), may change these values.

1. Modified sample size.
2. Modified for speed, sample width (2.54 cm/1 in.) and gauge length.
3. Modified for sealing fluid characteristics.

**Tyvek**<sup>®</sup>  
For greater good™

[medicalpackaging.dupont.com](http://medicalpackaging.dupont.com)  
[medicalpackaging.dupont.com/linkedin](http://medicalpackaging.dupont.com/linkedin)  
1 800 44 TYVEK

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is intended for use by persons having technical skill for evaluation under their specific end-use conditions at their own discretion and risk. Since conditions of use are outside our control, **DuPont makes no warranties, expressed or implied, including without limitations, no warranties of merchantability or fitness for a particular use and assumes no liability in connection with any use of this information.** This information is not intended as a license to operate under or a recommendation to infringe any patent, trademark or technical information of DuPont or others covering any material or its use. DuPont®, the DuPont Oval Logo, For greater good™ and Tyvek® are trademarks or registered trademarks of DuPont or its affiliates. Copyright © 2019 DuPont de Nemours Inc. (05/19)