



BETASEAL™ 1527EP



60-minute minimum drive away at -10°C

- 60-minute minimum drive away in temperatures from -10°C to 40°C
- High-modulus formula helps maintain structural integrity at original equipment levels
- Non-conductive urethane reduces interference with radio, mobile phone, GPS or additional driver aid technologies
- No heating required for improved work efficiency
- Improved formula is easy to use with excellent decking and short cut-off string
- Choice of three sizes – 310 ml cartridge or 400 ml or 600 ml sausage packs



www.dupont.com/aftermarket



BETASEAL™ 1527EP – improved formulation delivers outstanding performance and is even easier to use

60-minute minimum drive away at -10 °C

A 60-minute minimum drive away ensures a secure finish even on cold days. Yet at these low temperatures, BETASEAL™ 1527EP remains easy to gun and doesn't require heating. The improved formula promotes superior decking and short cut-off string.

High-modulus formula promotes structural integrity

The high-modulus formula helps promote the car's structural integrity and stabilization to improve the ride and reduce rattles, vibrations and other vehicle noises. It's also non-conductive so it reduces interference with radio, mobile phone, GPS or additional driver aid technologies.

More information

For more information on how BETASEAL™ 1580 and AINS technology can help your customers get back on the road, visit www.dupont.com.

Physical Properties	BETASEAL™ 1527EP*
Minimum Drive-Away Time	60 minutes
G Modulus	>2.1 MPa
Conductivity	Non-conductive
Bulk Resistivity	1 x 10 ¹⁰ Ωcm
Working Time	10-12 minutes
Material Temperature Range	-5°C to 40°C
Ambient Temperature Range	-10°C to 40°C
Extrudability	Easy with professional dispensers
Storage Stability	9-month shelf life

*Results based on DuPont internal testing.

Easy-to-use: Clean, Prime and Bond

Clean

Bonding surfaces must be clean of dirt, dust, water, oil, silicone and grease prior to priming and adhesive application. Use BETACLEAN™ Easy-Go Sponge to help remove contaminants from glass and BETACLEAN™ 3300 to inspect and

Prime

Priming of the glass and aperture is required before application of BETASEAL™ 1527EP. BETAPRIME™ 5504G is an all-in-one primer suitable for all surfaces: cut-back PU bead, aperture, glass and ceramic frit.

Bond

BETASEAL™ Adhesives are easy to gun in most weather conditions and do not require heating.



dupont.com/aftermarket



DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2024 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Form No. 001-20990-OIA0224