

# DuPont™ BQ221

## Carbon Conductive Composition

### Product Description

DuPont™ BQ221 is a highly active carbon conductor designed as a working electrode for high sensitivity biosensor. It may be used on both PET and Polycarbonate substrates

### Product Benefits

- High Sensitivity
- Low Resistivity
- Compatible with variety of silver conductors

### Processing

#### Screen Printing Equipment

Reel-to-reel, semi-automatic or manual

#### Ink Residence Time on Screen

>1 Hour

#### Screen Types

Polyester, stainless steel

#### Typical Cure Conditions

Box oven: 130°C for 5-10 minutes

Reel-to-reel: 140°C for 1 minute

#### Typical Circuit Line Thickness Printed with 200-mesh Stainless Steel Screen

8-12 microns

#### Clean-Up Solvent

Ethylene diacetate or methyl propasol acetate

**Table 1 - Composition Properties**

Test	Properties
Solids (150°C) [%]	32.0 - 34.0
Viscosity (Pa.S) [Brookfield RVT, spindle#14, 10rpm, 25°C]	35-85
Coverage (cm²/g @ 12.5 microns)	200
Thinner	DuPont™ 8260

**Table 2 - Typical Physical Properties on 5-mil Polyester Film**

Test	Properties
Sheet Resistivity (mΩ/sq/mil)	< 100
PET, untreated (B)	5
Abrasion Resistance, Pencil Hardness (H) (ASTM D3363-74)	4
Solder	Not Recommended

Tables 1 and 2 show anticipated typical physical properties for DuPont™ BQ221 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

### Storage and Shelf Life

BQ Series compositions should be stored in a clean, stable environment at room temperature (~25°C) with their lids tightly sealed. Storage in high temperature (>30°C) or in freezers (<0°C) is NOT recommended as this could cause irreversible changes in the material. The shelf life of compositions in factory-sealed (unopened) containers stored under room temperature (~25°C) conditions is 6 months from the date of shipment. Some settling of solids may occur over time, so composition should be stirred thoroughly before use.

### Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).



**[electronics.dupont.com](http://electronics.dupont.com)**

For more information on DuPont™ BQ221 or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5.

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

EI-10090 (03/21)