

DuPont 5018

UV Curable Dielectric

Product Description

DuPont 5018 is a UV curable, solvent less, screen printable composition used in encapsulant and crossover applications for both rigid and flexible circuit manufacture. It offers the advantages of rapid cure and excellent processing latitude while maintaining excellent electrical and physical properties after cure, including excellent crosshatch adhesion to print-treated and good adhesion to non-print-treated PET substrate and conductor. It is fully compatible with DuPont's 5000's Series conductor compositions.

Product Benefits

- Fast UV cure
- Zero VOC when properly cured

Processing

Screen Printing Equipment

Semiautomatic and manual

Substrates

Polyester, polyimide, epoxy glass

Ink Residence Time on Screen

> 2 hours

Screen Types

Polyester, stainless steel

Optimum Cure Conditions for Flexibility

40 ft/min in air¹

500 - 1500 mJ/cm²*

Typical Thickness (after cure per print) Printed with 200 - 280 mesh stainless steel screen

1-1.2 mil

Two prints of dielectric are strongly recommended to achieve maximum circuit reliability.

¹RPC Industries "QC" Processor Model 1202 AN, with the 200 W/in medium- pressure mercury vapor lamps. Since cure conditions govern characteristics, customers should establish the cure rate required to produce optimum combination of flexibility and hardness.

*0.500 - 1.500, joules using International Light IL390B Light Bug or UV Process Supply Con-Trol-Cure® Compact Radiometer, or 0.100 - 0.300 joules, using Electronic Instrumentation & Technology Inc. UR 365 CHI Radiometer

Table 1 - Typical Physical Properties and Electrical Properties on Polyester Film

Test	Properties
Adhesion Crosshatch (ASTM D3359-78) Dielectric to Polyester Scotch Tape#600	No Transfer (5B)
Conductor to Dielectric	No transfer
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	≥ 1
Operating Use Temperature (°C)	At least 70
Flexibility (180° crease over DuPont 5007)	No opens
Breakdown Voltage (ASTM D150)[V/mil DC]	≥ 500
Dielectric Constant (ASTM D150)[@ 1KHz]	4.4
Insulation Resistance [GΩ/sq/mil]	> 10
Change in Physical Properties after Environmental Tests*	Insignificant
Change in Electrical Properties after Environmental Tests*	May drop up to one order of magnitude

* Environmental Tests

• Thermal Shock (+85°C to -40°C, 30 min. each, 5 cycles)

• Dry Heat (+85°C, 10 days)

• Humidity (+40°C, 95% RH, 10 days) [MIL Std 202E, method 103, cond. A]

• Salt Spray (+35°C, 5% salt, 10 days) [ASTM B117]

Tables 1 & 2 show anticipated typical physical properties for DuPont 5018 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

DuPont 5018

UV Curable Dielectric

Table 2 - Composition Properties

Test	Properties
Viscosity (Pa.s) [Brookfield 0.5RVT, 10 rpm, #14 spindle, 25°C]	15 - 30
Solids (150°C)[%]	100
Coverage (cm ² /g) (Dependent on print thickness):	
0.45 mil coating given by 280-mesh polyester	500
0.6 mil coating given by 230-mesh polyester	375
1.0 mil coating given by 280-mesh stainless steel	290
1.1 mil coating given by 200-mesh stainless steel	240
Thinner	Not recommended
Density, g/cm ³	1.28
Color	Blue
Odor	Slight, pleasant

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For information on health and safety regulations please refer to the specific product MSDS.



electronics.dupont.com

For more information on DuPont 5018 or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5..

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

EI-10177 (03/21)