

# DuPont 5085

## Silver Carbon Conductive Composition

### Product Description

DuPont 5085 is a silver/carbon used to fabricate low-voltage circuitry, especially on flexible substrates. This composition has been specifically designed for applications involving biosensors where high conductivity is not required. DuPont 5085 has also been designed for fast-curing applications.

### Product Benefits

- Excellent adhesion to polycarbonate
- Fast cure

### Processing

#### Screen Printing Equipment

Reel-to-reel, Semi-automatic, manual

#### Substrates

Polyester, polyimide, paper, epoxy glass, Polycarbonate

#### Ink Residence Time on Screen

> 1 hour

#### Screen Types

Polyester, stainless steel

#### Typical Cure Conditions

Box oven: 130°C for 5-6 minutes

Reel-to-reel: 140°C for 1 minute

#### Typical Circuit Line Thickness Printed with 280-mesh Stainless Steel Screen

8-10 microns

#### Clean up Solvent

Ethylene glycol diacetate

**Table 1 - Typical Physical Properties on 5-mil Polyester Film**

Test	Properties
Sheet Resistivity (mΩ/sq/mil)	40 - 120
Resistivity after Flex(mΩ/sq/mil) 15 sec after test Crease (180°, 1 cycle)	< 500
Abrasion/Tape Pull (3M Scotch Tape #810)	No Material Transfer
Abrasion Resistance, Pencil Hardness (H) (ASTM D3363-74)	≥ 1
Operating Use Temperature (°C)	≤ 90
Solder	Not Recommended

**Table 2 - Composition Properties**

Test	Properties
Viscosity (Pa.S) [Brookfield 1/2 RVT, 10rpm #14 spindle, 25°C]	20 - 50
Solids (750°C) (%)	41.0 - 44.0
Coverage (cm <sup>2</sup> /g) [Dependent on screen size and material]	140 - 300
Thinner	DuPont 3610

Tables 1 & 2 show anticipated typical physical properties for DuPont 5085 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

# DuPont 5085

Silver Carbon Conductive Composition

## Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Avoid high heat (>30°C) or freezing. Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

## Safety and Handling

For information on health and safety regulations please refer to the specific product MSDS.



[electronics.dupont.com](http://electronics.dupont.com)

For more information on DuPont 5085 or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5..

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

EI-10178 (03/21)