

DuPont 7102

Carbon Conductive Composition

Product Description

DuPont 7102 carbon is used as conductor in designs that tolerate high resistivity. Major benefits include low cost and excellent screen life and high-temp stability. It can be used with semi-automatic and manual printers. DuPont 7102 may be blended with these DuPont compositions to meet specific resistance requirements: DuPont 7082 Carbon, DuPont 5028 Ag and DuPont 3571 Dielectric.

Product Benefits

- Low resistivity carbon
- High stability
- Superior activity in biomedical applications
- Excellent adhesion to polycarbonate substrates

Processing

Screen Printing Equipment

Semiautomatic, manual

Ink Residence Time on Screen

> 2 hours

Screen Types

Stainless steel, Polyester

Typical Cure Conditions

Box Oven: 120°C for 5 - 6 minutes

Typical Circuit Line Thickness Printed with 200-mesh stainless steel screen

9 - 15 microns

Clean-up Solvent

Ethylene diacetate or methyl propasol acetate

Table 1 - Typical Physical Properties on 5-mil Polyester Film

Test	Properties
Sheet Resistivity ($\Omega/\text{sq}/\text{mil}$)	20 - 30
Resistivity after Flex ($\Omega/\text{sq}/\text{mil}$) 15 sec after test Crease (180°, 1 cycle)	50
Abrasion Resistance, Pencil Hardness (ASTM D3363-74) [H]	2

Table 2 - Typical Composition Properties

Test	Properties
Viscosity (Pa.S) (Brookfield HBT, 10 rpm, #14 spindle & UC, 25°C)	60 - 125
Solids (150°C)(%)	34.5 - 37.5
Coverage ($\text{cm}^2/\text{g}/\text{mil}$)	103
Thinner	DuPont 3610

Tables 1 & 2 show anticipated typical physical properties for DuPont 7102 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For Safety and Handling information pertaining to this product, read the Material Safety Data Sheet (MSDS).

DuPont 7102

Carbon Conductive Composition



electronics.dupont.com

For more information on DuPont 7102 or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5..

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

EI-10185 (03/21)