

DuPont 5880

Silver/Silver Chloride Composition for Screen Printing

Product Description

DuPont 5880 is a solvent-based silver/silver chloride composition designed for screen printing onto polyester film. It is suitable for use as an electrode or a reference counter electrode for electrochemical sensors.

Product Benefits

- Low electrode polarization
- High Conductivity
- Excellent stability on contact with hi salt gels

Processing

Printing

DuPont 5870 5880 should be thoroughly mixed with a plastic or coated spatula before use. If settling is found after long storage, mix and then jar-roll composition sample overnight before use. It is best to use a polyester screen when printing to minimize contact with reactive metals.

Drying

Box oven: 120°C for 8-10 minutes
Reel-to-reel: 140°C for 3-4 minutes

Clean up Solvent

Ethylene glycol diacetate or dipropylene glycol methyl ether.

Thinner

DuPont 8210 may be used sparingly for slight adjustments to viscosity or to replace evaporation losses. However, the use of too much thinner or of a non-recommended thinner may affect the rheological behaviour of the material and its printing characteristics.

Equipment Consideration

Polyester film substrates should be used. DuPont 5880 can also be printed over silver (DuPont 5000, DuPont 5025) or over carbon (DuPont 7105). Care should be taken to minimize contact of silver/silver chloride compositions with metals, especially reactive metals such as aluminum or brass, no contact should occur. Components made of these materials can be protected by taping or covering with an inert material.

Table 1 - Typical Physical Properties

Test	Properties
Density (g/cc)	3.25
Cross Hatch Adhesion (B) [ASTM Norm D3359078]	5
Coverage (cm ² /g) [Printed with 325 stainless steel mesh]	Approx. 200
EKG Properties	
DC offset (mV)	<5
AC Impedence (Ω)	<60
Resistivity (mΩ/sq/mil)	25

Table 2 - Composition Properties

Test	Properties
Viscosity (Pa.S) [Brookfield 0.5 RVT, Utility cup & spindle SC4- 14/6R, 10 rpm, 25°C]	30 - 60
Solids (150°C)[%]	84.0 - 86.0
Thinner	DuPont 8210
Ag:AgCl ratio	80/20

Tables 1 & 2 show anticipated typical physical properties for DuPont 5880 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Storage and Shelf Life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25°C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior to use.

Safety and Handling

For information on health and safety regulations please refer to the specific product MSDS.

DuPont 5880

Silver/Silver Chloride Composition for Screen Printing



electronics.dupont.com

For more information on DuPont 5880 or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5..

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

EI-10197 (03/21)