

# AmberLyst™ Polymeric Catalysts



## AmberLyst™ Polymeric Catalysts

Application & Product Name	Type	Matrix	Surface Area <sup>[1]</sup> (m <sup>2</sup> /g)	Avg. Pore Diameter <sup>[1]</sup> (Å)	Minimum Capacity (eq/L)	(eq/kg) <sup>[2]</sup>	Water Retention Capacity (%)	Shipping Weight (g/L) (lb/ft <sup>3</sup> )		Recommended Max. Op. Temperature (°C) (°F)	
<b>Etherification (MTBE, ETBE, TAME)</b>											
AmberLyst™ 15WET	Strong acid	Macro	53	300	1.80	4.70	52 – 57	770	48.1	120	250
AmberLyst™ 35WET	Strong acid	Macro	50	300	1.90	5.20	51 – 57	800	49.9	150	300
AmberLyst™ 17	Strong acid	Macro	30	200	1.85	4.90	50 – 54	760	47.4	120	250
<b>Dimerization (Isooctane)</b>											
AmberLyst™ 35WET	Strong acid	Macro	50	300	1.90	5.20	51 – 57	800	49.9	150	300
AmberLyst™ 36WET	Strong acid	Macro	33	240	1.95	5.40	51 – 57	800	49.9	150	300
<b>Phenol Purification</b>											
AmberLyst™ 16WET	Strong acid	Macro	30	250	1.70	4.80	52 – 58	780	48.7	130	265
AmberLyst™ 36WET	Strong acid	Macro	33	240	1.95	5.40	51 – 57	800	49.9	150	300
<b>Phenol Alkylation</b>											
AmberLyst™ 15DRY	Strong acid	Macro	53	300	-	4.70	≤ 1.6	610	38.1	120	250
AmberLyst™ 35DRY	Strong acid	Macro	50	300	-	5.00	≤ 3.0	560	35.0	150	300
AmberLyst™ 36DRY	Strong acid	Macro	33	240	-	5.40	≤ 1.65	770	48.1	150	300
AmberLyst™ 17DRY	Strong acid	Macro	30	200	-	4.70	≤ 3.0	590	36.8	120	250
<b>Condensation (Bisphenol-A)</b>											
AmberLyst™ 33	Strong acid	Gel	-	-	1.35	5.00	64 – 68	732	45.7	130	265
AmberLyst™ 125	Strong acid	Gel	-	-	0.70	4.80	77 – 83	730	45.6	130	265
<b>Pre-promoted Catalysts</b>											
AmberLyst™ 125B	Strong acid	Gel	-	-	0.70	4.80	77 – 83	714	44.6	130	265
AmberLyst™ 131B	Strong acid	Gel	-	-	1.35	4.80	62 – 68	770	48.1	130	265
<b>Hydrogenation (MIBK, TAME)</b>											
AmberLyst™ CH10	Strong acid (Pd)	Macro	33	240	1.60	4.80	52 – 58	790	49.3	130	265
AmberLyst™ CH28	Strong acid (Pd)	Macro	36	260	1.60	4.80	52 – 58	790	49.3	130	265
AmberLyst™ CH33	Strong acid (Pd)	Macro	36	260	1.60	4.80	52 – 58	790	49.3	130	265
<b>Olefin Hydration (TBA, IPA, SBA)</b>											
AmberLyst™ 15WET	Strong acid	Macro	53	300	1.80	4.70	52 – 57	770	48.1	120	250
AmberLyst™ 45	Strong acid	Macro	49	190	1.00	2.95	51 – 55	770	48.1	170	340
<b>Esterification (Acetates, Acrylates, Fatty Acid Esters)</b>											
AmberLyst™ 15WET	Strong acid	Macro	53	300	1.80	4.70	52 – 57	770	48.1	120	250
AmberLyst™ 16WET	Strong acid	Macro	30	250	1.70	4.80	52 – 58	780	48.7	130	265
AmberLyst™ 36WET	Strong acid	Macro	33	240	1.95	5.40	51 – 57	800	49.9	150	300
AmberLyst™ 39WET	Strong acid	Macro	32	230	1.15	5.00	60 – 66	735	45.9	130	265
AmberLyst™ 46	Strong acid	Macro	75	235	-	0.80	26 – 36	600	37.5	120	250
AmberLyst™ 45	Strong acid	Macro	49	190	1.00	2.95	51 – 55	770	48.1	170	340
AmberLyst™ 131WET	Strong acid	Gel	-	-	1.35	4.80	62 – 68	740	46.2	130	265
AmberLyst™ 19	Strong acid	Gel	-	-	1.80	-	48 – 54	785	49.0	120	250
<b>Base Catalyzed Reactions</b>											
AmberLyst™ A21	Weak base	Macro	35	110	1.30	4.60	56 – 62	660	41.2	100 <sup>[3]</sup>	210
AmberLyst™ A26 OH	Strong base Type I	Macro	30	290	0.80	4.20	66 – 75	675	42.1	60 <sup>[4]</sup>	140
AmberLyst™ A21DRY	Weak base	Macro	35	110	-	5.00	≤ 0.3	330	20.6	100 <sup>[3]</sup>	210
AmberLyst™ A22	Weak base	Macro	55	290	1.70	-	40 – 50	640	40.0	120 <sup>[3]</sup>	250

<sup>[1]</sup> Nitrogen BET    <sup>[2]</sup> Dry weight    <sup>[3]</sup> Free base form    <sup>[4]</sup> Hydroxide form

## Remarks

Etherification catalyst. Extremely resistant to breakdown by osmotic and mechanical shock.

Excellent etherification catalyst. Higher acid strength, better performance, and longer lifetime than conventional catalysts.

Uniform particle size catalyst offering reduced pressure drop and higher throughput for increased production.

Dimerization catalyst with high activity and high temperature stability.

Dimerization catalyst that combines high activity, high temperature stability, and good resistance to polymer fouling.

Condensation catalyst. A low degree of crosslinking provides a high resistance to polymer fouling.

Higher exchange capacity and improved thermal stability compared to conventional catalysts.

Alkylation catalyst. Excellent for use in non-aqueous systems where the presence of water has a negative effect on catalyst activity.

Alkylation catalyst with higher acidity and improved thermal stability compared to conventional catalysts.

Exceptional alkylation catalyst. In addition to high thermal stability, the low degree of crosslinking confers a high resistance to organic fouling.

Uniform particle size, dry catalyst offering reduced pressure drop and increased productivity.

Very low acid leachables, designed for high-purity BPA production.

Low crosslinked, uniform large bead size catalyst that offers excellent productivity with good resistance to polymer fouling.

Pre-promoted, uniform large bead size catalyst for reduced pressure drop. Promotion level: 17 – 23%.

Excellent pre-promoted catalyst with uniform particle size which confers enhanced hydraulic properties and reactivity compared to conventional catalysts. Promotion level: 22 – 28%.

Bifunctional catalyst with acid and metal functionality; contains 1.0 g/L Pd. Used primarily in TAME production to selectively hydrogenate diolefins.

Bifunctional catalyst with acid and metal functionality; contains 2.8 g/L Pd. Used primarily for MIBK production.

Bifunctional catalyst with acid and metal functionality; contains 3.3 g/L Pd. Used primarily for MIBK production.

Conventional hydration catalyst suitable for reactive olefins such as isobutylene.

High-temperature catalyst for the synthesis of SBA and IPA.

Catalyst for low molecular weight acetate esters.

Best suited catalyst for medium molecular weight esters. Used in industrial production of butyl acrylate and methyl methacrylate.

Highly active catalyst with high temperature stability. Well suited for fatty acid esterification.

Esterification catalyst for higher molecular weight compounds that diffuse slowly into conventional catalysts.

Patented esterification catalyst that minimizes by-product formation such as ethers or olefins.

High-temperature catalyst for the synthesis of high molecular weight esters and the esterification of diols and polyols.

Excellent catalyst for low molecular weight esters. Used for ethyl acrylate production.

Highly active esterification catalyst for the reaction of acrylic acid with methanol and ethanol to form the corresponding acrylates.

Macroporous, weak base anion catalyst.

Excellent choice for aldol condensation. High resistance to organic fouling.

Ready-to-use catalyst for silane disproportionation.

High-capacity, macroporous, weak base anion catalyst.



# Powering performance worldwide.

With a large global manufacturing footprint, strong R&D expertise and technical support services and systems, we supply high market volumes with high quality. DuPont partners with you, our customer, to understand unmet needs and develop tailored solutions.

## TECHNICAL SERVICE, RESEARCH & DEVELOPMENT

Chauny, France  
Edina, MN, USA  
Huzhou, China  
Hyderabad, India  
KAUST Jeddah, KSA  
Midland, MI, USA  
Shanghai, China  
Singapore  
Tarragona, Spain\*  
Wilmington, DE, USA

## COMMERCIAL OPERATIONS

Astana, Kazakhstan  
Bangkok, Thailand  
Beijing, China  
Bogota, Colombia  
Buenos Aires, Argentina  
Budapest, Hungary  
Dubai, UAE  
Chengdu, China  
Delhi, India  
Edina, MN, USA  
Guangzhou, China  
HCM City, Vietnam  
Hong Kong, China  
Jakarta, Indonesia  
Johannesburg, South Africa  
Kuala Lumpur, Malaysia  
Madrid, Spain

Manila, Philippine  
Melbourne, Australia  
Mexico City, Mexico  
Midland, MI, USA  
Moscow, Russia  
Mumbai, India  
Nairobi, Kenya  
Paris, France  
São Paulo, Brazil  
Seoul, Republic of Korea  
Pfaeffikon, Switzerland  
Shanghai, China  
Singapore  
Surubya, Indonesia  
Taipei, Taiwan  
Tokyo, Japan  
Warsaw, Poland

## MANUFACTURING

Chauny, France  
Edina, MN, USA  
Fombio, Italy  
Huzhou, China  
Jubail Industry City,  
Saudi Arabia  
Midland, MI, USA  
Qingpu, China  
Soma, Japan

\* Global Water  
Technology Center

**Have a question?** Contact us at: [dupont.com/water/contact-us](https://www.dupont.com/water/contact-us)



[dupont.com/water](https://www.dupont.com/water)

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2019 DuPont.

Form No. 45-D01063-en CDP, Rev. 3  
December 2019