

Stator Cooling Circuit

Product Recommendations

The stator cooling circuit requires careful control of its chemistry (pH, dissolved oxygen, dissolved copper) in order to provide efficient cooling, little corrosion, and no deposition of corrosion

products in the cooling elements. Ion exchange resins are used to control the chemistry of the loop by increasing or decreasing pH, lowering conductivity, and removing dissolved copper.

Product	Features and Recommended Uses	Type	Matrix	Minimum Total Volume Capacity (eq/L)	Ionic Form as Shipped
Individual Resins for Customized Chemistry Control¹					
AmberLite™ HPR550 OH	High capacity uniform particle size gel type anion resin. Paired best with AmberLite™ HPR650 H or AmberLite™ HPR1300 Na depending on the preferred operational method.	SBA	GEL	1.10	OH
AmberLite™ HPR1300 Na	High capacity uniform particle size gel type cation resin. Sodium form cation is best used for enhanced pH control. Paired best with AmberLite™ HPR550 OH to be used to increase the pH of the purification loop while still removing copper and other cation impurities	SAC	GEL	2.20	Na+
AmberLite™ HPR650 H	A high capacity uniform gel cation resin for removal of copper and other cation impurities and pH control. Paired best with AmberLite™ HPR550 OH to be used when neutral pH is targeted.	SAC	GEL	2.00	H+
Ready to Use Mixed Beds					
AmberLite™ IRN150 H/OH	Nuclear grade mixed bed composed of uniform particle size AmberLite™ IRN77 H and IRN78 OH on a 1:1 equivalent basis for full demineralization.	MB	GEL/GEL	1.90/1.20	H+/OH ⁻
AmberLite™ IRN160 H/OH	High capacity nuclear grade mixed bed composed of uniform particle size AmberLite™ IRN97 H and IRN78 OH on a 1:1 equivalent basis. Designed to minimize separation of anion and cation during installation and transfer in stator cooling applications	MB	GEL/GEL	2.10/1.20	H+/OH ⁻
AmberLite™ IRN170 H/OH	Premium nuclear grade mixed bed composed of uniform particle size AmberLite™ IRN99 H and IRN78 OH on a 1:1 equivalent basis. Offers maximum oxidative stability and highest operating capacity to achieve the lowest ionic leakage and longest resin life.	MB	GEL/GEL	2.50/1.20	H+/OH ⁻

Key:

¹= The individual cation and anion must be prepared in-situ.

SBA = Strong Base Anion

SAC = Strong Acid Cation

MB = Mixed Bed

Powering performance worldwide.

With a large global manufacturing footprint, strong R&D expertise and technical support services and systems, we supply high market volumes with high quality. DuPont partners with you, our customer, to understand unmet needs and develop tailored solutions.

TECHNICAL SERVICE, RESEARCH & DEVELOPMENT

Chauny, France
Edina, MN, USA
Huzhou, China
Hyderabad, India
KAUST Jeddah, KSA
Midland, MI, USA
Shanghai, China
Singapore
Tarragona, Spain*
Wilmington, DE, USA

COMMERCIAL OPERATIONS

Astana, Kazakhstan
Bangkok, Thailand
Beijing, China
Bogota, Colombia
Buenos Aires, Argentina
Budapest, Hungary
Dubai, UAE
Chengdu, China
Delhi, India
Edina, MN, USA
Guangzhou, China
HCM City, Vietnam
Hong Kong, China
Jakarta, Indonesia
Johannesburg, South Africa
Kuala Lumpur, Malaysia
Madrid, Spain

Manila, Philippine
Melbourne, Australia
Mexico City, Mexico
Midland, MI, USA
Moscow, Russia
Mumbai, India
Nairobi, Kenya
Paris, France
São Paulo, Brazil
Seoul, Republic of Korea
Pfaeffikon, Switzerland
Shanghai, China
Singapore
Surabaya, Indonesia
Taipei, Taiwan
Tokyo, Japan
Warsaw, Poland

MANUFACTURING

Chauny, France
Edina, MN, USA
Fombio, Italy
Huzhou, China
Jubail Industry City,
Saudi Arabia
Midland, MI, USA
Qingpu, China
Soma, Japan

* Global Water
Technology Center

Have a question? Contact us at: [dupont.com/water/contact-us](https://www.dupont.com/water/contact-us)



[dupont.com/water](https://www.dupont.com/water)

No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

DuPont™, the DuPont Oval Logo, and all products denoted with ® or ™ are trademarks or registered trademarks of DuPont or its affiliates Copyright © 2020 DuPont de Nemours.

45-D01487-en 0220 CDP